

TECAPEEK® PVX black - Stock Shapes (rods, plates, tubes)

Chemical Designation

PEEK (Polyetheretherketone)

Colour

black opaque

Density

1.46 g/cm³

Fillers

carbon fibres, PTFE, graphite

Main features

- good heat deflection temperature
- high creep resistance
- good slide and wear properties
- hydrolysis and superheated steam resistant
- inherent flame resistance
- excellent chemical resistance

Target Industries

- mechanical engineering
- chemical technology
- conveyor technology
- automotive industry
- textile industry
- precision engineering
- aircraft and aerospace technology

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	800,000	psi	ASTM D 638	(1) data from injection molded samples publicly sourced
Tensile strength at yield	@ 73 °F	11,000	psi	ASTM D 638	(2) injection molded data, publicly sourced data
Elongation at break (tensile test)	@ 73 °F	2.5	%	ASTM D 638	(3) injection molded data from public source
Flexural strength	@ 73 °F	18,000	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F Tangent	700,000	psi	ASTM D 790	
Compression strength	@ 10% strain, 73 °F	16,500	psi	ASTM D 695	
Compression modulus	@ 73 °F	330,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	0.90	ft-lbs/in	ASTM D 256	
Rockwell hardness	M Scale	95		ASTM D 785	
Rockwell hardness	R Scale	119		ASTM D 785	
Coefficient of friction	@ 68 °F Static, 40 psi	0.18		ASTM D 3702	1)
Coefficient of friction	@ 68 °F Dynamic 40 psi 50 fpm	0.20		ASTM D 3702	2)
Wear rate	@ 68 °F 40 psi, 50 fpm	10	*10 ⁻¹⁰ in ³ -min/ft-lb-hr	ASTM D 3702	3)
Thermal properties	condition	value	unit	test method	comment
Melting temperature		633	°F	-	(1) Data obtained from public source
Deflection temperature	@264 psi	530	°F	ASTM D 648	(2) Data obtained from public source
Service temperature	Max Continuous Use	500	°F	-	
Service temperature	short term	572	°F	-	1)
Thermal expansion (CLTE)		3.11	*10 ⁻⁵ in/in/°F	ASTM D 696	
Thermal conductivity		5.69	BTU-in/hr-ft ² -°F	-	2)
Electrical properties	condition	value	unit	test method	comment
surface resistivity		1.4*10 ⁵	Ω/square	ASTM D 257	
Other properties	condition	value	unit	test method	comment
Limiting PV	@ 68 °F	500000		ASTM D 3702	1)
Moisture absorption	@ 24 hrs, 73 °F	0.02	%	ASTM D 570	(1) injection molded sample, data from public source
Moisture absorption	@ saturation, 73 °F	0.03	%	ASTM D 570	(2) Estimate
Flammability (UL94)		V0		-	2)

→ Resin specification:
ASTM D4000-11 PAEK0000R30D73200
Shapes specification:
ASTM D6262-12 S-PAEK0140R30

→ TECAPEEK products are based on Victrex® PEEK polymer.

→ Resin specification:
ASTM D4000-11 PAEK0000R30D73200
Shapes specification:
ASTM D6262-12 S-PAEK0140R30

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.