

TECAPEEK® ST - Stock Shapes (rods, plates, tubes)

Chemical Designation

PEKEKK
(Polyetherketoneetherketoneketone)

Colour

black

Density

1.32 g/cm³

Main features

- made exclusively from Victrex® resin
- high heat deflection temperature
- excellent mechanical properties
- excellent chemical resistance
- easy to machine
- good dimensional stability
- electrically insulating
- high purity

Target Industries

- oil and gas industry
- semiconductor technology
- chemical plant engineering
- automotive industry
- process engineering

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	(0.2 in/min)	760,000	psi	ASTM D 638	
Tensile strength at yield	0.2 in/min	19,400	psi	ASTM D 638	
Elongation at break (tensile test)	0.2 in/min	15	%	ASTM D 638	
Flexural strength	@ 73 °F	31,000	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	740,000	psi	ASTM D 790	
Compression strength	10% Strain	24,400	psi	ASTM D 695	
Compression strength	1% Strain	2,860	psi	ASTM D 695	
Compression modulus		445,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	0.8	ft-lbs/in	ASTM D 256	
Rockwell hardness	R Scale	112		ASTM D 785	
Thermal properties	condition	value	unit	test method	comment
Glass transition temperature		324	°F	DIN EN ISO 11357	1) (1) Injection molded data
Melting temperature		729	°F	DIN EN ISO 11357	2) (2) Injection molded data
Deflection temperature	@264 psi	342	°F	ISO-R 75 Method A	3) (3) ISO 75-f Injection molded data
Service temperature	Long Term	500	°F	-	4) (4) Data obtained from public source
Service temperature	short term	572	°F	-	
Thermal expansion (CLTE)		2.72	*10 ⁻⁵ in/in/°F	ASTM E 831	
Electrical properties	condition	value	unit	test method	comment
surface resistivity		1.0*10 ¹⁴	Ω/square	-	1) (1) Data obtained from public source
volume resistance		>10 ¹⁵	Ω*cm	DIN IEC 60093	
Other properties	condition	value	unit	test method	comment
Moisture absorption	@ saturation, 50% R.H.	0.05	%	ASTM D 570	1) (1) Data obtained from public source
Moisture absorption	@ 24 hrs., 73°F	0.02	%	ASTM D 570	1) (2) Data obtained from public source
Flammability (UL94)		V0		-	2) (2) Data obtained from public source

→ TECAPEEK products are based on Victrex® PEEK polymer.

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters
365 Meadowslands Boulevard
Washington, PA 15301, USA

Phone 800-243-3221 Sales
Phone 800-869-4029 Technical
Fax 724-746-9209
sales@ensingerusa.com

Date: 2017/09/07

Version: A2