

FORMPLAST® 2000 - Stock Shapes (rods, plates, tubes)

Chemical Designation

PU (Polyurethane)

Colour

light blue

Density

1.2 g/cm³

Main features

- excellent impact strength
- high toughness
- easily machinable to tight tolerance
- very good mechanical strength

Target Industries

- packaging and paper machinery

Mechanical properties	condition	value	unit	test method	comment	
Modulus of elasticity (tensile test)	1% Sec, @ 73 °F	260,000	psi	ASTM D 638		
Tensile strength at yield	@ 73 °F	10,000	psi	ASTM D 638		
Flexural strength	@ 73 °F	13,000	psi	ASTM D 790		
Modulus of elasticity (flexural test)	Tangent @ 73 °F	320,000	psi	ASTM D 790		
Compression strength	@ 73 °F	12,000	psi	ASTM D 695		
Impact strength (Izod)	@ 73 °F	7.0	ft-lbs/in	ASTM D 256		
Thermal properties	condition	value	unit	test method	comment	
Vicat softening point		291	°F	-	1)	(1) publicly sourced data
Deflection temperature	@264 psi, 1/4	241	°F	ASTM D 648	2)	(2) publicly sourced data
Service temperature	Long Term	280	°F	-	3)	(3) Injection molded data
Thermal expansion (CLTE)		3.7*10 ⁻⁵	in/in/°F	ASTM D 696	4)	(4) publicly sourced data
Specific heat		0.26	BTU/lb-F°	-	5)	(5) publicly sourced data
Thermal conductivity		0.322	W/(K*m)	-	6)	(6) publicly sourced data

→ Resin specification:
Ensinger Internal Specification
Shapes specification:
NONE

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters
365 Meadowlands Boulevard
Washington, PA 15301, USA

Phone 800-243-3221 Sales
Phone 800-869-4029 Technical
Fax 724-746-9209
sales@ensingerusa.com

Date: 2016/12/27

Version: A0