

## TECAST® L MO dark blue - Stock Shapes (rods, plates, tubes)

### Chemical Designation

PA 6 (Polyamide 6)

### Colour

dark blue

### Density

1.15 g/cm<sup>3</sup>

### Fillers

oil, molybdenum disulfide

### Main features

- very good bearing and wear properties
- excellent slip-stick properties
- designed for minimal chatter
- very good mechanical strength
- high fatigue strength
- resistant to many oils, greases and fuels

### Target Industries

- construction industry
- heavy duty industry

Mechanical properties	condition	value	unit	test method	comment
Tensile strength	@ 73°F	8,700	psi	ASTM D 638	(1) Data obtained from public source
Modulus of elasticity (tensile test)	@ 73 °F	280,000	psi	-	(2) data from public sources (3) data from public sources
Elongation at break (tensile test)	@ 73 °F	75	%	ASTM D 638	
Flexural strength	@ 73 °F	8,300	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	250,000	psi	ASTM D 790	
Compression modulus	@ 73 °F	406,000	psi	ASTM D 638	1)
Impact strength (Izod)	@ 73 °F	1.27	ft-lbs/in	ASTM D 256	
Rockwell hardness	R Scale	110		ASTM D 785	
Coefficient of friction	Static	0.16		-	2)
Coefficient of friction	Dynamic	0.14		-	3)
Thermal properties	condition	value	unit	test method	comment
Melting temperature		428	°F	-	1)
Service temperature	Long Term	200	°F	-	(1) Data obtained from public sources (2) data from public sources
Service temperature	Intermittent	330	°F	-	
Thermal expansion (CLTE)		4.0	*10 <sup>-5</sup> in/in/°F	ASTM D 696	2)
Other properties	condition	value	unit	test method	comment
Limiting PV		17,000	psi-ft/min	-	1)
Moisture absorption	@ 24 hrs.	0.5	%	ASTM D 570	2)
Moisture absorption	@ saturation, 73°F	4	%	ASTM D 570	3)

→ Resin specification:  
NONE  
Shapes specification:  
ASTM D5989-11 S-PA0200

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com).

Ensinger Inc. Headquarters  
365 Meadowlands Boulevard  
Washington, PA 15301, USA

Phone 800-243-3221 Sales  
Phone 800-869-4029 Technical  
Fax 724-746-9209  
[sales@ensingerusa.com](mailto:sales@ensingerusa.com)

Date: 2016/10/24

Version: A1