

TECAPEEK® CF30 black - Stock Shapes (rods, plates, tubes)

Chemical Designation

PEEK (Polyetheretherketone)

Colour

black opaque

Density

1.41 g/cm³

Fillers

30% carbon fibres

Main features

- very good chemical resistance
- good heat deflection temperature
- inherent flame resistance
- hydrolysis and superheated steam resistant
- very high stiffness
- very high creep resistant
- high dimensional stability
- resistance against high energy radiation

Target Industries

- aircraft and aerospace technology
- automotive industry
- conveyor technology
- oil and gas industry
- mechanical engineering
- chemical plant engineering

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	920,000	psi	ASTM D 638	(1) Data from public source (2) data from public source (3) Data from public source (4) per ASTM D3846
Tensile strength at yield	@ 73 °F	17,500	psi	ASTM D 638	
Elongation at break (tensile test)	@ 73 °F	7.0	%	ASTM D 638	
Flexural strength	@ 73 °F	28,000	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	1,040,000	psi	ASTM D 790	
Compression strength	@ 10% strain, 73 F	24,000	psi	ASTM D 695	
Compression strength	@1% strain, 73 °F	2,700	psi	ASTM D 695	
Compression modulus	@ 73 °F	489,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	1.16	ft-lbs/in	ASTM D 256	
Rockwell hardness	M Scale	107		ASTM D 785	
Coefficient of friction	@ 68 °F, Static, 50 psi	0.19		ASTM D 3702	1)
Coefficient of friction	Dynamic, 40 psi, 50 fpm	0.13		ASTM D 3702	2)
Wear (K) factor	40 psi, 50 fpm	60	*10 ⁻¹⁰ in ³ -min/ft-lb-hr	ASTM D 3702	3)
Shear strength	@ 73 °F	14,100	psi	-	4)
Thermal properties	condition	value	unit	test method	comment
Melting temperature		633	°F	-	1)
Deflection temperature	@264 psi, 1/4	600	°F	ASTM D 648	2)
Service temperature	Long Term	500	°F	-	3)
Service temperature	short term	572	°F	-	4)
Thermal expansion (CLTE)		0.80	*10 ⁻⁵ in/in/°F	ASTM D 696	5)
Thermal conductivity		6.37	BTU-in/hr-ft ² -°F	ASTM C 177	6)
Electrical properties	condition	value	unit	test method	comment
surface resistivity		1.0*10 ⁸	Ω/square	-	1)
Other properties	condition	value	unit	test method	comment
Limiting PV	@ 68 °F	385,000	psi-fpm	-	1)
Moisture absorption	@ 24 hrs, 73 °F	0.06	%	ASTM D 570	(1) 1200 in/min (2) Estimated
Flammability (UL94)		V0	%	-	2)

→ TECAPEEK products are based on Victrex® PEEK polymer.

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.