

HYDEX® 301 natural - Stock Shapes (rods, plates, tubes)

Chemical Designation

PU (Polyurethane)

Colour

yellow transparent

Density

1.2 %

Main features

- broad chemical compatibility
- very good dimensional stability
- good impact strength
- good mechanical properties
- high toughness

Target Industries

- medical technology
- chemical plant engineering
- oil and gas industry
- pharmaceutical industry
- cleanroom technology

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	310,000	psi	ASTM D 638	(1) publicly sourced data (2) publicly sourced data (3) publicly sourced data (4) publicly sourced data (5) publicly sourced data
Tensile strength at yield	@ 73 °F	10,000	psi	ASTM D 638	1)
Tensile strength at break	@ 73 °F	9,000	psi	ASTM D 638	2)
Elongation at yield (tensile test)	@ 73 °F	7	%	ASTM D 638	3)
Elongation at break (tensile test)	@ 73 °F	150	%	ASTM D 638	
Flexural strength	@ 73 °F	14,500	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	320,000	psi	ASTM D 790	
Compression strength	@ 73 °F, 1% strain	1,200	psi	ASTM D 695	
Compression strength	@ 73 °F, 10% strain	11,700	psi	ASTM D 695	
Compression modulus	@ 73 °F	230,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	1.10	ft-lbs/in	ASTM D 256	
Rockwell hardness	M	95	-	-	
Coefficient of friction	Static (vs. steel)	0.22		ASTM D 3702	4)
Coefficient of friction	Dynamic (vs. steel)	0.21		ASTM D 3702	5)
Thermal properties	condition	value	unit	test method	comment
Vicat softening point		228	°F	ASTM D 1525	1)
Deflection temperature	@ 66 psi	190	°F	ASTM D 648	2)
Deflection temperature	@ 264 psi	170	°F	ASTM D 648	3)
Service temperature	Long Term	170	°F	-	4)
Thermal expansion (CLTE)		3.4*10 ⁻⁵	in/in/°F	ASTM D 696	5)
Other properties	condition	value	unit	test method	comment
Moisture absorption	@ 24 hrs, 73 °F	0.10	%	ASTM D 570	

→ Resin specification:
Ensinger Internal Specification
Shapes specification:
NONE

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters
365 Meadowlands Boulevard
Washington, PA 15301, USA

Phone 800-243-3221 Sales
Phone 800-869-4029 Technical
Fax 724-746-9209
sales@ensingerusa.com

Date: 2021/06/16

Version: A1