

TECAPEEK ST black - 型材(棒材,板材,管件)

化學命名

PEKEKK (聚醚酮醚酮酮)

顏色

黑色 不透明

密度

1.32 g/cm³

主要特色

- 高熱與機械能力
- 優異的耐化學性
- 良好的加工特性
- 良好的熱變形溫度
- 良好的尺寸穩定性
- 低吸濕性

目標產業

- 化學技術
- 機械工程
- 汽車工業

機械特性

參數	值	單位	標準	註解
抗拉強度	50mm/min	134	MPa	DIN EN ISO 527-2
彈性模數 (張力測試)	1mm/min	4600	MPa	DIN EN ISO 527-2 1)
降伏點抗拉強度	50mm/min	134	MPa	DIN EN ISO 527-2
降伏點伸長率	50mm/min	5	%	DIN EN ISO 527-2
斷裂伸長率	50mm/min	13	%	DIN EN ISO 527-2
抗彎強度	2mm/min, 10 N	193	MPa	DIN EN ISO 178 2)
彈性模數 (彎曲測試)	2mm/min, 10 N	4600	MPa	DIN EN ISO 178
壓縮強度	1% / 2% / 5% 5mm/min, 10 N	24/42/98	MPa	EN ISO 604 3)
壓縮模數	5mm/min, 10 N	3500	MPa	EN ISO 604 4)
衝擊強度(Charpy)	max. 7,5J	n.b.	kJ/m ²	DIN EN ISO 179-1eU 5)
缺口衝擊強度(Charpy)	max. 7,5J	4	kJ/m ²	DIN EN ISO 179-1eA
蕭氏硬度	D	90		DIN EN ISO 868

熱特性

參數	值	單位	標準	註解
玻璃轉化溫度	165	°C	DIN EN ISO 11357	1)
熔化溫度	384	°C	DIN EN ISO 11357	
使用溫度 short term	300	°C		2)
使用溫度 long term	260	°C		
熱膨脹 (CLTE)	23-60°C, long.	5	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2
熱膨脹 (CLTE)	23-100°C, long.	5	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2
熱膨脹 (CLTE)	100-150°C, long.	6	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2

電性特性

參數	值	單位	標準	註解
表面電阻	10 ¹⁴	Ω	-	

其他特性

參數	值	單位	標準	註解
吸水率	24h / 96h (23°C)	0.02 / 0.03	%	DIN EN ISO 62 1)
耐熱水/鹼	+	-		2)
耐候性	(+)	-		3)
耐燃性(UL94)	corresponding to	V0		DIN IEC 60695-11-10; 4)

→ TECAPEEK 產品是使用 Victrex® PEEK 原物料製作而成。

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.