

## TECATRON PPS CM XP83 black - 型材 (棒材, 板材, 管件)

### 化學命名

PPS (聚苯硫醚)

### 顏色

黑色 不透明

### 密度

1.43 g/cm<sup>3</sup>

### 添加物

碳纖維, 石墨, 鐵氟龍

生產製程: 壓縮成型

### 主要特色

- 良好的尺寸穩定性
- 良好的耐化學性
- 高蠕變抗性
- 良好的熱變形溫度
- 高能輻射抗性
- 高剛性
- 高強度

### 目標產業

- 石油和天然氣工業

機械特性	參數	值	單位	標準	註解
抗拉強度		35	MPa	ASTM D 638	
斷裂伸長率		1.5	%	ASTM D 638	
抗彎強度		53	MPa	ASTM D 790	
蕭氏硬度	Shore D	88	MPa	ASTM D 2240	

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on compression moulded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensinger-online.com](http://www.ensinger-online.com). Technical changes reserved.

時間: 2019/01/07

版本: AC