

## TECAFINE® PP natural - Stock Shapes (rods, plates, tubes)

### Chemical Designation

PP (Polypropylene)

### Colour

white

### Density

0.9 g/cm<sup>3</sup>

### Main features

- excellent chemical resistance
- high purity
- good mechanical properties
- very low water absorption

### Target Industries

- chemical plant engineering
- cleanroom technology
- food processing
- food engineering
- pharmaceutical industry
- filter technology
- nuclear and vacuum technology

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Modulus of elasticity (tensile test)	@ 73 °F	105,000	psi	ASTM D 638	
Tensile strength at break	@ 73 °F	3,900	psi	ASTM D 638	
Elongation at break (tensile test)	@ 73 °F	500	%	ASTM D 638	
Flexural strength	@ 73 °F	4,500	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	165,000	psi	ASTM D 790	
Notched impact strength (Izod)	@ 73 °F	2.1	ft-lbs/in	ASTM D 256	
Rockwell hardness	R Scale	102		ASTM D 785	
Rockwell hardness	M Scale, @ 73 °F	95		-	
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Melting temperature		297	°F	-	1) (1) per ASTM D3418
Deflection temperature	@66 psi	165	°F	ASTM D 648	2) (2) Resin data
<i>Other properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Moisture absorption	@ 24 hrs, 73 °F	0.06	%	ASTM D 570	

→ Resin specification:  
ASTM D4101-10a PP0210  
Shapes specification:  
NONE

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com).

Ensinger Inc. Headquarters  
365 Meadowlands Boulevard  
Washington, PA 15301, USA

Phone 800-243-3221 Sales  
Phone 800-869-4029 Technical  
Fax 724-746-9209  
[sales@ensingerusa.com](mailto:sales@ensingerusa.com)

Date: 2017/10/04

Version: A1