

TECAPEEK® GF30 natural - Stock Shapes (rods, plates, tubes)

Chemical Designation

PEEK (Polyetheretherketone)

Colour

natural opaque

Density

1.53 g/cm³

Fillers

30% glass fibres

Main features

- good heat deflection temperature
- very good chemical resistance
- very high creep resistant
- hydrolysis and superheated steam resistant
- inherent flame resistance
- very high stiffness
- high dimensional stability
- resistance against high energy radiation

Target Industries

- agricultural machinery
- aircraft and aerospace interiors
- aircraft and aerospace technology
- food processing
- food engineering
- automotive industry
- electrical engineering
- chemical plant engineering
- mechanical engineering
- conveyor technology

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	1% Sec. @ 73 °F	1,000,000	psi	ASTM D 638	(1) Data obtained from public source
Tensile strength at yield	@ 73 °F	15,000	psi	ASTM D 638	(2) Injection molded specimen data obtained from public source
Tensile strength at break	@ 73 °F	15,000	psi	ASTM D 638	(3) injection molded specimen data from public source
Elongation at break (tensile test)	@ 73 °F	2.2	%	ASTM D 638	(4) injection molded specimen data from public source
Flexural strength	@ 73 °F	24,000	psi	ASTM D 790	(5) per ASTM D3846
Modulus of elasticity (flexural test)	@ 73 °F	1,000,000	psi	ASTM D 790	
Compression strength	@ 10% strain, 73 °F	25,000	psi	ASTM D 695	
Compression modulus	@ 73 °F	696,000	psi	ASTM D 695	1)
Impact strength (Izod)	@ 73 °F	1.8	ft-lbs/in	ASTM D 256	
Rockwell hardness	M Scale	103		ASTM D 785	
Coefficient of friction	@ 68 °F, Static, 50 psi	0.28		ASTM D 3702	2)
Coefficient of friction	@ 68 °F, Dynamic, 40 psi, 50 fpm	0.30		ASTM D 3702	3)
Wear (K) factor	@ 68 °F, 40 psi, 50 fpm	90*10 ⁻¹⁰	in ³ -min/ft-lbs-hr	ASTM D 3702	4)
Shear strength	@ 73 °F	14,100	psi	-	5)
Thermal properties	condition	value	unit	test method	comment
Melting temperature		633	°F	-	1)
Deflection temperature	@264 psi, 1/4	600	°F	ASTM D 648	2)
Service temperature	Long Term	500	°F	-	3)
Service temperature	short term	572	°F	-	4)
Thermal expansion (CLTE)	< Tg, along flow	1.2*10 ⁻⁵	in/in/°F	DIN EN ISO 11359-1;2	5)
Thermal conductivity		2.08	BTU-in/hr-ft ² -°F	ISO 22007-4:2008	6)
Electrical properties	condition	value	unit	test method	comment
surface resistivity		1.0*10 ¹⁶	Ω/square	ASTM D 257	(1) injection molded specimen from public source
volume resistance	@ 73 °F	1.0*10 ¹⁶	Ω*cm	ASTM D 149	(2) injection molded specimen from public source
Dielectric strength	0.1	790	V/mil	ISO 60243-1	(3) injection molded specimen from public source
Dissipation factor	@ 73 °F, 1 MHz	0.005		DIN IEC 60250	
Dielectric constant	@ 73 °F, 1 kHz	3.2		DIN IEC 60250	
Other properties	condition	value	unit	test method	comment
Moisture absorption	@ 24 hrs, 73 °F	0.2	%	ASTM D 570	(1) Data obtained from public source
Moisture absorption	@ saturation, 73°F	0.3	%	ASTM D 570	(2) Injection molded 3mm specimen
Flammability (UL94)		V0		-	

→ Resin specification:
ASTM D4000-11 PEEK; MIL-P-46183 Ty. II Cl. 3, excp. Elong.
Shapes specification:
ASTM D6262-12 S-PAEK0121

→ TECAPEEK products are based on Victrex® PEEK polymer.

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.