

TECACOMP PPS TRM XS black 1014938 - Compounds

Chemical Designation

PPS (Polyphenylsulfide)

Colour

black

Density

1.47 g/cm³

Fillers

carbon fibres, solid lubricant

Main features

→ very good bearing and wear properties

Target Industries

→ automotive industry
→ mechanical engineering

Mechanical properties	parameter	value	unit	norm	comment
Tensile strength	50 mm/min	135	MPa	DIN EN ISO 527-1	
Modulus of elasticity (tensile test)	50 mm/min	22500	MPa	DIN EN ISO 527-1	
Elongation at break (tensile test)	50 mm/min	0,5	%	DIN EN ISO 527-1	
Compression strength	5 mm/min	155	MPa	EN ISO 604	
Compression modulus	1 mm/min	4650	MPa	EN ISO 604	
Impact strength (Charpy)		18	kJ/m ²	DIN EN ISO 179-1eU	
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		90	°C	DIN 53765	
Melting temperature		280	°C	DIN 53765	
Heat distortion temperature	HDT A	280	°C	ISO-R 75 Method A	
Heat distortion temperature	HDT B	285	°C	ISO-R 75 Method B	
Service temperature	short term	260	°C	-	
Service temperature	long term	230	°C	-	
Thermal expansion (CLTE)	longitudinal (at 23 - 80 °C)	9	10 ⁻⁶ K ⁻¹	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	transverse (at 23 - 80 °C)	47	10 ⁻⁶ K ⁻¹	DIN EN ISO 11359-1;2	
Thermal conductivity	in-plane	1,1	W/(K*m)	DIN EN 821	
Thermal conductivity	through-plane	0,7	W/(K*m)	DIN EN 821	
Electrical properties	parameter	value	unit	norm	comment
volume resistivity		6,2 x 10 ¹	Ω*m	DIN EN ISO 3915	
Other properties	parameter	value	unit	norm	comment
Water absorption	23 °C / 50 % relative humidity up to saturation	< 0,1	%	DIN EN ISO 62	(1) No listing at UL (Yellow Card).
Molding shrinkage	longitudinal	0,13	%	DIN EN ISO 294-4	
Molding shrinkage	transverse	0,64	%	DIN EN ISO 294-4	
Flammability (UL94)		V0		DIN IEC 60695-11-10;	1)
Melt flow index (MFI)	316 °C / 2,16 kg	35	g/10 min	DIN EN ISO 1133	
MVR	316 °C / 2,16 kg	29	cm ³ /10 min	DIN EN ISO 1133	
Bulk density		0,55	g/cm ³	EN ISO 60	
Processing parameter	parameter	value	unit	norm	comment
Cylinder/processing temperature		300 - 350	°C	-	
Mould temperature		140 - 160	°C	-	
Material temperature		335 - 360	°C	-	

- This material can be processed as a thermoplastic taking the normal technical provisions into account. The above mentioned information refers exclusively to the injection moulding process.
- Processing should be carried out as gently as possible, in order to maintain the maximum fibre length in the component. Back pressure and injection rate should be adjusted to the component geometry accordingly. The optimum processing temperature depends upon the respective geometry of the moulded part and can be different from machine to machine.

Pre-drying	parameter	value	unit	norm	comment
Permissible residual moisture content		< 0,05	%	-	
Drying temperature		140 - 150	°C	-	
Drying time		4 - 6	h	-	

- To achieve optimum mechanical properties, it is recommended to pre-dry the material with the above mentioned parameters.
- Information on storage and shelf life: The granules must be stored in dry, normally tempered rooms and in closed containers. For moisture-sensitive materials, the granules must be sealed airtight. Protection against direct sunlight must be guaranteed. The granules are usually subject to the requirements of no shelf life limitation. Shelf Life may be limited by some additives.

Our information and statements reflect to current state of our knowledge and shall inform about the products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for the use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests on injection moulded samples, dry as moulded. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at ensingerplastics.com. Technical changes reserved.

