

TECAPEEK CMF white - Stock Shapes (rods, plates, tubes)

Chemical Designation

PEEK (Polyetheretherketone)

Colour

white

Density

1.63 g/cm³

Fillers

ceramic

Main features

- high dimensional stability
- good machinability
- high strength
- high stiffness
- low thermal expansion
- low burring
- good heat deflection temperature
- very good thermal stability

Target Industries

- electrical engineering
- precision engineering
- semiconductor technology
- vacuum technology

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	1,227,111	psi	ASTM D 638	1) (1) All properties derived from machined plate test specimens
Tensile strength at yield	@ 73 °F	14,122	psi	ASTM D 638	(2) Data obtained from public source
Tensile strength at break	50 mm/min	15,200	psi	DIN EN ISO 527-2	(3) Data obtained from public source
Elongation at yield (tensile test)	50 mm/min	3	%	DIN EN ISO 527-1	
Elongation at break (tensile test)	@ 73 °F	4.85	%	ASTM D 638	
Flexural strength	@ 73 °F	23,642	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	783,585	psi	ASTM D 790	
Compression strength	@ 73 °F @ 1% strain	1,855	psi	ASTM D 695	
Compression strength	@ 73 °F @ 10% strain	20,712	psi	ASTM D 695	
Compression modulus	@ 73 °F	335,369	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F notched	0.66	ft-lbs/in	ASTM D 256	
Impact strength (Izod)	@ 73 °F unnotched	15.23	ft-lbs/in	ASTM D 256	
Rockwell hardness	M-Scale	102		ASTM D 785	
Thermal properties	condition	value	unit	test method	comment
Melting temperature		643	°F	-	1) (1) ASTM D3418
Service temperature	Long Term	500	°F	-	(2) Data obtained from public source
Service temperature	short term	500	°F	-	
Thermal expansion (CLTE)	73 F to 140 F	2.23	*10 ⁻⁵ in/in/°F	ASTM E 831	
Thermal expansion (CLTE)	73 F to 212 F	2.27	*10 ⁻⁵ in/in/°F	ASTM E 831	
Thermal expansion (CLTE)	212 F to 302 F	2.58	*10 ⁻⁵ in/in/°F	ASTM E 831	
Thermal conductivity		2.60	BTU-in/hr-ft ² -°F	ASTM E1530	
Electrical properties	condition	value	unit	test method	comment
surface resistivity		5.2E+15	Ω/square	ASTM D 257	
volume resistance		3.5E+15	Ω*cm	ASTM D 257	
Dielectric strength	S/T, in oil	168	V/mil	ASTM D 149	
Dissipation factor	1 MHz dry	0.0032		ASTM D 150	
Dielectric constant	1 MHz dry	4.71		ASTM D 150	
Other properties	condition	value	unit	test method	comment
Moisture absorption	@ 24 hrs	0.03	%	ASTM D 570	(1) Data obtained from public source
Flammability (UL94)		V0		-	1)

→ TECAPEEK products are based on Victrex® PEEK polymer.

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.