

TECAPEEK SD black - 型材 (棒材, 板材, 管件)

化學命名
PEEK (聚醚醚酮)

顏色
黑色 不透明

密度
1.71 g/cm³

主要特色

→ 靜電放電
→ 絕佳的耐化學性

目標產業

→ 半導體科技

機械特性	參數	值	單位	標準	註解
抗拉強度	50mm/min	91	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
彈性模數 (張力測試)	1mm/min	5800	MPa	DIN EN ISO 527-2	(2) For flexural test: support span 64mm, norm specimen.
斷裂伸長率	50mm/min	2	%	DIN EN ISO 527-2	(3) Specimen 10x10x10mm
抗彎強度	2mm/min, 10 N	148	MPa	DIN EN ISO 178	(4) For Charpy test: support span 64mm, norm specimen.
彈性模數 (彎曲測試)	2mm/min, 10 N	5600	MPa	DIN EN ISO 178	
壓縮強度	1% / 2% 5mm/min, 10 N	28 / 53	MPa	EN ISO 604	
衝擊強度(Charpy)	max. 7,5J	43	kJ/m ²	DIN EN ISO 179-1eU	
蕭氏硬度	D	91		DIN EN ISO 868	
熱特性	參數	值	單位	標準	註解
玻璃轉化溫度		151	°C	DIN EN ISO 11357	(1) Found in public sources.
熔化溫度		341	°C	DIN EN ISO 11357	
使用溫度	short term	300	°C	DIN 53765	
使用溫度	long term	260	°C	DIN 53765	
熱膨脹 (CLTE)	23-60°C, long.	5	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
熱膨脹 (CLTE)	23-100°C, long.	5	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
熱膨脹 (CLTE)	100-150°C, long.	7	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
電性特性	參數	值	單位	標準	註解
表面電阻		10 ⁶ - 10 ⁹	Ω	DIN EN 61340-2-3	
其他特性	參數	值	單位	標準	註解
吸水率	24h / 96h (23°C)	0.02 / 0.03	%	DIN EN ISO 62	(1) Ø ca. 50mm, h=13mm
耐燃性(UL94)		V0		-	

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.