

TECASON P MT XRO blue - Stock Shapes (rods, plates, tubes)

Chemical Designation

PPSU (Polyphenylsulfone)

Colour

blue opaque

Density

1.35 g/cm³

Fillers

barium sulfate

Main features

- x-ray opaque
- high thermal and mechanical capacity
- hydrolysis and superheated steam resistant
- good impact strength
- high stiffness
- high strength
- good chemical resistance
- high gamma radiation resistance

Target Industries

- medical technology

Mechanical properties	parameter	value	unit	norm	comment
Tensile strength	50mm/min	79	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
Modulus of elasticity (tensile test)	1mm/min	2400	MPa	DIN EN ISO 527-2	1) (2) For flexural test: support span 64mm, norm specimen.
Tensile strength at yield	50mm/min	79	MPa	DIN EN ISO 527-2	(3) For Charpy test: support span 64mm, norm specimen.
Elongation at yield (tensile test)	50mm/min	7	%	DIN EN ISO 527-2	n.b. = not broken
Elongation at break (tensile test)	50mm/min	> 50	%	DIN EN ISO 527-2	
Flexural strength	2mm/min, 10 N	104	MPa	DIN EN ISO 178	2)
Modulus of elasticity (flexural test)	2mm/min, 10 N	2400	MPa	DIN EN ISO 178	
Impact strength (Charpy)	max. 7,5J	n.b.	kJ/m ²	DIN EN ISO 179-1eU	3)
Notched impact strength (Charpy)	max. 7,5J	12	kJ/m ²	DIN EN ISO 179-1eA	
Shore hardness	D	84		DIN EN ISO 868	
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		218	°C	DIN EN ISO 11357	1) (1) Found in public sources.
Service temperature	short term	190	°C		2) (2) Found in public sources.
Service temperature	long term	170	°C		Individual testing regarding application conditions is mandatory.
Other properties	parameter	value	unit	norm	comment
Water absorption	24h / 96h (23°C)	0.1 / 0.2	%	DIN EN ISO 62	1) (1) Ø ca. 50mm, h=13mm
Resistance to hot water/ bases		+			2) (2) + good resistance
Resistance to weathering		-			3) (3) - poor resistance
Flammability (UL94)	corresponding to	V0		DIN IEC 60695-11-10;	4) (4) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.