

## TECAST T blue - Stock Shapes (rods, plates, tubes)

### Chemical Designation

PA 6 C (Cast polyamide 6)

### Colour

blue

### Density

1.15 g/cm<sup>3</sup>

Data generated directly after machining  
(standard climate Germany).

### Main features

- good wear properties
- good mechanical properties
- high fatigue strength
- good damping
- high mechanical load capacity
- resistant to many oils, greases and fuels

### Target Industries

- construction industry
- gear manufacturing
- oil and gas industry
- conveyor technology
- agricultural machinery
- heavy duty industry
- mining industry

<b>Mechanical properties</b>	<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Tensile strength	50mm/min	89	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
Modulus of elasticity (tensile test)	1mm/min	3600	MPa	DIN EN ISO 527-2	1)
Tensile strength at yield	50mm/min	89	MPa	DIN EN ISO 527-2	
Elongation at yield (tensile test)	50mm/min	18	%	DIN EN ISO 527-2	
Elongation at break (tensile test)	50mm/min	25	%	DIN EN ISO 527-2	
Shore hardness	D	82		DIN EN ISO 868	
<b>Thermal properties</b>	<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Glass transition temperature		49	°C	DIN EN ISO 11357	(1) Found in public sources. Individual testing regarding application conditions is mandatory.
Melting temperature		217	°C	DIN EN ISO 11357	(2) Found in public sources.
Service temperature	short term	170	°C	-	1)
Service temperature	long term	100	°C	-	
Thermal expansion (CLTE)	23-60°C, long.	11	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	2)
Specific heat		1.6	J/(g*K)	ISO 22007-4:2008	
Thermal conductivity		0.33	W/(K*m)	ISO 22007-4:2008	
<b>Electrical properties</b>	<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
surface resistivity		10 <sup>14</sup>	Ω	DIN IEC 60093	
<b>Other properties</b>	<b>parameter</b>	<b>value</b>	<b>unit</b>	<b>norm</b>	<b>comment</b>
Moisture absorption	24h / 96h (23°C)	0.2 / 0.5	%	DIN EN ISO 62	1) (1) Ø ca. 50mm, h=13mm 2) (+) limited resistance 3) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Resistance to hot water/ bases		(+)		-	2)
Resistance to weathering		(+)		-	
Flammability (UL94)	corresponding to	HB		DIN IEC 60695-11-10;	3)

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on cast and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com). Technical changes reserved.