

## TECAPEEK IM natural - Stock Shapes (rods, plates, tubes)

### Chemical Designation

PEEK (Polyetheretherketone)

### Colour

brown-beige

### Density

1.44

### Main features

- excellent chemical resistance
- excellent mechanical properties
- high thermal resistance
- good heat deflection temperature
- good machinability
- very good slide and wear properties
- hydrolysis and superheated steam resistant

### Target Industries

- oil and gas industry
- aircraft and aerospace technology
- food technology
- food processing
- chemical plant engineering
- semiconductor technology
- automotive industry

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	@73°F	537,000	psi	ASTM D 638	
Tensile strength at yield	@73°F	14,500	psi	ASTM D 638	
Elongation at break (tensile test)	@73°F	45	%	ASTM D 638	
Flexural strength	@73°F	23,900	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@73°F	595,000	psi	ASTM D 790	
Compression strength	@73°F	18,100	psi	ASTM D 695	
Impact strength (Charpy)	@73°F	21.4	ft-lbs/in	-	
Thermal properties	condition	value	unit	test method	comment
Melting temperature		649	°F	-	
Service temperature	Long Term	500	°F	-	
Service temperature	Short Term	572	°F	-	
Thermal expansion (CLTE)		2.5*10 <sup>-5</sup>	in/in/°F	DIN EN ISO 11359-1;2	
Electrical properties	condition	value	unit	test method	comment
surface resistivity	@73°F	1.0*10 <sup>16</sup>	Ω/square	ASTM D 257	
volume resistance	@73°F	4.9*10 <sup>16</sup>	Ω*cm	ASTM D 149	
Dielectric strength	0.1" thick IEC 60243-1	630	V/mil	ISO 60243-1	
Dissipation factor	@73°F, 1MKz	0.003		DIN IEC 60250	
Dielectric constant	@73°F, 1kHz	2.8		DIN IEC 60250	
Other properties	condition	value	unit	test method	comment
Flammability (UL94)		V0		-	

→ Resin specification:  
ASTM D4000-11 PEEK; MIL-P-46183 Ty. I  
Shapes specification:  
ASTM D6262-12 S-PAEK0111

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com).

Ensinger Inc. Headquarters  
365 Meadowlands Boulevard  
Washington, PA 15301, USA

Phone 800-243-3221 Sales  
Phone 800-869-4029 Technical  
Fax 724-746-9209  
[sales@ensingerusa.com](mailto:sales@ensingerusa.com)

Date: 2018/08/07

Version: A0