

## TECASINT 5511 SD light-brown - halvfabrikat

### Kemisk beteckning

PI (polyimid)

### Färg

Brun

### Densitet

1.65 g/cm<sup>3</sup>

### Fillers

glas fibrer

### Huvud egenskaper

- elektriskt statisk dissipativ
- hög termisk och mekanisk kapacitet
- låg termisk expansion
- högt krypmotstånd
- motstånd mot hög energi strålning

### Målindustrier

- elektronik
- halvledartechnik
- kryogenteknik
- elektroteknik
- maskinteknik
- kärn- och vakuumteknik

Mekaniska Egenskaper	parameter	värde	enhet	norm	anmärkning
Draghållfasthet	50 mm/min, 23°C	97	MPa	DIN EN ISO 527-1	
Elasticitetsmodul (dragprov)	1 mm/min, 23°C	5600	MPa	DIN EN ISO 527-1	
Brottförlängning	50 mm/min, 23°C	2,1	%	DIN EN ISO 527-1	
Böjhållfasthet	10 mm/min, 23°C	128	MPa	DIN EN ISO 178	
Elasticitetsmodul (böjningstest)	2 mm/min, 23°C	5588	MPa	DIN EN ISO 178	
Brottförlängning (böjtest)	10 mm/min, 23°C	2,3	%	DIN EN ISO 178	
Kompressionsstyrka	10 mm/min, 23°C	254	MPa	EN ISO 604	
tryckhållfasthet vid brott	10 mm/min, 23°C	21,4	%	EN ISO 604	
Kompressionsmodul	1 mm/min	5890	MPa	EN ISO 604	
Shore hårdhet	Shore D, 23°C	92		DIN EN ISO 868	
Värmeledningsförmåga	parameter	värde	enhet	norm	anmärkning
Glasövergångstemperatur		329	°C	DIN EN ISO 11357	(1) Found in public sources.
Service temperatur	lower operating temperature	- 20	°C	-	1) Individual testing regarding application conditions is mandatory.
Service temperatur	short-term	300	°C	-	2) (2) Found in public sources.
Service temperatur	long-term	250	°C	-	3) Individual testing regarding application conditions is mandatory.
termisk expansion	23-100°C	32	10 <sup>-6</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	4) (3) Found in public sources.
termisk expansion	100-150°C	35	10 <sup>-6</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	5) Individual testing regarding application conditions is mandatory.
termisk expansion	50-200°C	35	10 <sup>-6</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	6) (4) Thermal expansion XY axis
Specifik värme		1,01	J/(g*K)	DIN EN 821	(5) Thermal expansion XY axis
Värmeledningsförmåga	40°C	0,32	W/(K*m)	DIN EN 821	(6) Thermal expansion XY axis
Elektriska egenskaper	parameter	värde	enhet	norm	anmärkning
surface resistance	23°C	10 <sup>09</sup> - 10 <sup>11</sup>	Ω	ANSI ESD STM 11.11	
Specifikt ytmotstånd	23°C	10 <sup>10</sup> - 10 <sup>12</sup>	Ω/square	ANSI ESD STM 11.11	
Elektrisk resistans	23°C	10 <sup>09</sup> - 10 <sup>11</sup>	Ω	ANSI ESD STM 11.12	
Specifik volymresistans	23°C	10 <sup>10</sup> - 10 <sup>12</sup>	Ω*cm	ANSI ESD STM 11.12	
Övriga egenskaper	parameter	värde	enhet	norm	anmärkning
Vatten absorption	24 h in water, 23°C	0.60	%	DIN EN ISO 62	(1) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Brandklassning (UL94)	corresponding to	V0		DIN IEC 60695-11-10;	1)

→ TECASINT 5000 series show significant water uptake. Parts have to be pre-dried before fast heating to above 200 °C (drying process: 2 h per 3 mm wall thickness at 150 °C).

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com). Technical changes reserved.