

TECASINT 8591 grey - Stock Shapes (rods, plates, tubes)

Chemical Designation

PTFE (Polytetrafluorethylene)

Colour

grey

Density

2.56 g/cm³

Main features

- very good slide and wear properties
- low static friction
- high dimensional stability
- low outgassing
- very good thermal stability
- good chemical resistance

Target Industries

- aircraft and aerospace technology
- cryogenic engineering
- vacuum technology
- propulsion technology

<i>Mechanical properties</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Tensile strength	50 mm/min	13	MPa	DIN EN ISO 527-1	
Modulus of elasticity (tensile test)	1 mm/min	2300	MPa	DIN EN ISO 527-1	
Elongation at break (tensile test)	50 mm/min	20	%	DIN EN ISO 527-1	
Shore hardness	Shore D	67		DIN EN ISO 868	
Coefficient of friction		0,14 - 0,22		-	
Wear rate		1 - 10	10 ⁻⁶ mm ³ /Nm	-	
<i>Thermal properties</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Service temperature	long-term	260	°C	-	1) (1) Found in public sources. Individual testing regarding application conditions is mandatory.
Thermal expansion (CLTE)	23-100°C	53	10 ⁻⁶ K ⁻¹	DIN EN ISO 11359-1;2	2) (2) Expansión térmica eje XY
Thermal expansion (CLTE)	50-200°C	55	10 ⁻⁶ K ⁻¹	DIN EN ISO 11359-1;2	3) (3) Expansión térmica eje XY
Thermal expansion (CLTE)	100-150°C	52	10 ⁻⁶ K ⁻¹	DIN EN ISO 11359-1;2	4) (4) Thermal expansion XY axis
<i>Other properties</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Water absorption	24h / 96h (23°C)	0,003 / 0,016	%	DIN EN ISO 62	(1) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Outgassing in high vacuum		passed		ECSS-Q-70-02	
Flammability (UL94)	corresponding to	V0		DIN IEC 60695-11-10; 1)	

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.