

TECAFORM AH MT yellow - Stock Shapes (rods, plates, tubes)

Chemical Designation

POM-C (Polyacetal (Copolymer))

Colour

yellow opaque

Density

1.41 g/cm³

Main features

- electrically insulating
- biocompatible
- good chemical resistance
- good machinability
- high stiffness
- high toughness
- difficult to bond
- high strength

Target Industries

- medical technology
- food technology
- pharmaceutical industry

Mechanical properties

	parameter	value	unit	norm	comment
Tensile strength	50mm/min	69	MPa	DIN EN ISO 527-2	
Modulus of elasticity (tensile test)	1mm/min	2800	MPa	DIN EN ISO 527-2	1)
Tensile strength at yield	50mm/min	70	MPa	DIN EN ISO 527-2	
Elongation at yield (tensile test)	50mm/min	15	%	DIN EN ISO 527-2	
Elongation at break (tensile test)	50mm/min	30	%	DIN EN ISO 527-2	
Flexural strength	2mm/min, 10 N	94	MPa	DIN EN ISO 178	2)
Modulus of elasticity (flexural test)	2mm/min, 10 N	2800	MPa	DIN EN ISO 178	
Compression strength	1% / 2% / 5% 5mm/min, 10 N	18/32/65	MPa	EN ISO 604	3)
Compression modulus	5mm/min, 10 N	2200	MPa	EN ISO 604	4)
Impact strength (Charpy)	max. 7,5J	n.b.	kJ/m ²	DIN EN ISO 179-1eU	5)
Notched impact strength (Charpy)	max. 7,5J	9	kJ/m ²	DIN EN ISO 179-1eA	
Ball indentation hardness		158	MPa	ISO 2039-1	6)

Thermal properties

	parameter	value	unit	norm	comment
Glass transition temperature		-60	°C	DIN EN ISO 11357	1)
Melting temperature		169	°C	DIN EN ISO 11357	
Service temperature	short term	140	°C		2)
Service temperature	long term	100	°C		
Thermal expansion (CLTE)	23-60°C, long.	13	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	23-100°C, long.	14	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Specific heat	1.4	J/(g*K)		ISO 22007-4:2008	
Thermal conductivity	0.39	W/(K*m)		ISO 22007-4:2008	

Electrical properties

	parameter	value	unit	norm	comment
surface resistivity		> 10 ¹²		DIN IEC 60093	

Other properties

	parameter	value	unit	norm	comment
Water absorption	24h / 96h (23°C)	0.05 / 0.1	%	DIN EN ISO 62	1)
Resistance to hot water/ bases	(+)	-	-		2)
Resistance to weathering	-	-	-		3)
Flammability (UL94)	corresponding to	HB		DIN IEC 60695-11-10;	4)

- (1) Ø ca. 50mm, h=13mm
- (2) (+) limited resistance
- (3) - poor resistance
- (4) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.