

TECAPEEK CMF grey - Stock Shapes (rods, plates, tubes)

Chemical Designation

PEEK (Polyetheretherketone)

Colour

grey opaque

Density

1.65 g/cm³

Fillers

ceramic

Main features

- good machinability
- high strength
- high stiffness
- low thermal expansion
- low burring
- good heat deflection temperature
- very good thermal stability

Target Industries

- semiconductor technology
- electronics
- mechanical engineering
- vacuum technology

Mechanical properties	parameter	value	unit	norm	comment
Tensile strength	50mm/min	105	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
Modulus of elasticity (tensile test)	1mm/min	5500	MPa	DIN EN ISO 527-2	(2) For flexural test: support span 64mm, norm specimen.
Tensile strength at yield	50mm/min	102	MPa	DIN EN ISO 527-2	(3) Specimen 10x10x10mm
Elongation at yield (tensile test)	50mm/min	4	%	DIN EN ISO 527-2	(4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.
Elongation at break (tensile test)	50mm/min	5	%	DIN EN ISO 527-2	(5) For Charpy test: support span 64mm, norm specimen.
Flexural strength	2mm/min, 10 N	170	MPa	DIN EN ISO 178	(6) Specimen in 4mm thickness
Modulus of elasticity (flexural test)	2mm/min, 10 N	5500	MPa	DIN EN ISO 178	
Compression strength	1% / 2% / 5% 5mm/min, 10 N	25/46/105	MPa	EN ISO 604	(3)
Compression modulus	5mm/min, 10 N	4300	MPa	EN ISO 604	(4)
Impact strength (Charpy)	max. 7,5J	35	kJ/m ²	DIN EN ISO 179-1eU	(5)
Ball indentation hardness		286	MPa	ISO 2039-1	(6)
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		151	°C	DIN EN ISO 11357	(1)
Melting temperature		339	°C	DIN EN ISO 11357	(2)
Service temperature	short term	300	°C		(2)
Service temperature	long term	260	°C		
Thermal expansion (CLTE)	23-60°C, long.	5	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	23-100°C, long.	5	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	100-150°C, long.	6	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
Specific heat		1.0	J/(g*K)	ISO 22007-4:2008	
Thermal conductivity		0.38	W/(K*m)	ISO 22007-4:2008	
Electrical properties	parameter	value	unit	norm	comment
surface resistivity		10 ¹⁴	Ω	-	
volume resistivity		10 ¹⁴	Ω*cm	-	
Other properties	parameter	value	unit	norm	comment
Water absorption	24h / 96h (23°C)	0.02 / 0.03	%	DIN EN ISO 62	(1)
Resistance to hot water/ bases		+	-		(2)
Resistance to weathering		-	-		(3)
Flammability (UL94)	corresponding to	V0		DIN IEC 60695-11-10;	(4)

→ TECAPEEK products are based on Victrex® PEEK polymer.

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.