

TECAMID 6/3 TR natural - 型材 (棒材, 板材, 管件)

化學命名

PA 6-3-T (聚醯胺 6-3-T)

顏色

淺黃色 透明色

密度

1.12 g/cm³

加工後所產生的數據(依德國標準氣候為主)。

主要特色

- 高韌性
- 良好的耐化學性
- 良好的加工特性
- 良好的熱變形溫度
- 對壓力破裂敏感
- 高強度
- 易於研磨

目標產業

- 電子學
- 食品科技
- 機械工程
- 汽車工業

機械特性	參數	值	單位	標準	註解
抗拉強度	50mm/min	93	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
彈性模數 (張力測試)	1mm/min	2800	MPa	DIN EN ISO 527-2	(2) For flexural test: support span 64mm, norm specimen.
降伏點抗拉強度	50mm/min	93	MPa	DIN EN ISO 527-2	(3) Specimen 10x10x10mm
降伏點伸長率	50mm/min	7	%	DIN EN ISO 527-2	(4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.
斷裂伸長率	50mm/min	49	%	DIN EN ISO 527-2	(5) For Charpy test: support span 64mm, norm specimen.
抗彎強度	2mm/min, 10 N	117	MPa	DIN EN ISO 178	n.b. = not broken
彈性模數 (彎曲測試)	2mm/min, 10 N	2800	MPa	DIN EN ISO 178	(6) Specimen in 4mm thickness
壓縮強度	1% / 2% 5mm/min, 10 N	21 / 37	MPa	EN ISO 604	
壓縮模數	5mm/min, 10 N	2400	MPa	EN ISO 604	
衝擊強度(Charpy)	max. 7.5J	n.b.	kJ/m ²	DIN EN ISO 179-1eU	
缺口衝擊強度(Charpy)	max. 7.5J	7	kJ/m ²	DIN EN ISO 179-1eA	
球壓式硬度		150	MPa	ISO 2039-1	
熱特性	參數	值	單位	標準	註解
玻璃轉化溫度		148	°C	DIN EN ISO 11357	(1) Found in public sources.
熔化溫度		n.a.	°C	DIN EN ISO 11357	(2) n.a. = not applicable
使用溫度	short term	120	°C		(3) Found in public sources.
使用溫度	long term	100	°C		Individual testing regarding application conditions is mandatory.
熱膨脹 (CLTE)	23-60°C, long.	12	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
熱膨脹 (CLTE)	23-100°C, long.	12	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
比熱		1.6	J/(g*K)	ISO 22007-4:2008	
導熱係數		0.36	W/(K*m)	ISO 22007-4:2008	
電性特性	參數	值	單位	標準	註解
表面電阻		10 ¹⁴	Ω	-	
體積電阻		10 ¹⁴	Ω*cm	-	
其他特性	參數	值	單位	標準	註解
吸水率	24h / 96h (23°C)	0.3 / 0.6	%	DIN EN ISO 62	(1) Ø ca. 50mm, h=13mm
耐熱水/鹼		(+)	-	-	(2) (+) limited resistance
耐候性		-	-	-	(3) - poor resistance
耐燃性(UL94)	listed (value at 0.88mm)	V2	-	DIN IEC 60695-11-10;	(4) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.