

TECAPEEK CM XP98 black - Stock Shapes (rods, plates, tubes)

Chemical Designation

PEEK (Polyetheretherketone)

Colour

black opaque

Density

1.43 g/cm³

Fillers

carbon fibres

production process: compression moulding

Main features

- inherent flame retardant
- good heat deflection temperature
- hydrolysis and superheated steam resistant
- good machinability
- good slide and wear properties

Target Industries

- oil and gas industry

Mechanical properties	parameter	value	unit	norm	comment
Tensile strength		126	MPa	ASTM D 638	
Modulus of elasticity (tensile test)		9600	MPa	ASTM D 638	
Elongation at break (tensile test)		2.2	%	ASTM D 638	
Flexural strength		210	MPa	ASTM D 790	
Modulus of elasticity (flexural test)		11000	MPa	ASTM D 790	
Compression strength		181	MPa	ASTM D 695	
Shore hardness	Shore D	93		ASTM D 2240	
Thermal properties	parameter	value	unit	norm	comment
Melting temperature	DSC	342	°C	-	
Heat distortion temperature		> 237	°C	ASTM D 648	
Electrical properties	parameter	value	unit	norm	comment
surface resistivity		10 ⁶	Ω	-	

→ TECAPEEK products are based on Victrex® PEEK polymer.

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on compression moulded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.