

TECASINT 1011 natural - Stock Shapes (rods, plates, tubes)

Chemical Designation

PI (Polyimide)

Colour

black

Density

1.34 g/cm³

Main features

- high thermal and mechanical capacity
- very good thermal stability
- good chemical resistance
- very good electrical insulation
- resistance against high energy radiation
- low outgassing
- high creep resistance
- sensitive to hydrolysis in higher thermal range

Target Industries

- mechanical engineering
- precision engineering
- aircraft and aerospace technology
- cryogenic engineering
- electronics
- electrical engineering
- nuclear and vacuum technology
- semiconductor technology

Mechanical properties	parameter	value	unit	norm	comment
Tensile strength	50 mm/min	116	MPa	DIN EN ISO 527-1	(1) eU (2) eA
Modulus of elasticity (tensile test)	1 mm/min	3600	MPa	DIN EN ISO 527-1	
Elongation at break (tensile test)	50 mm/min	3.8	%	DIN EN ISO 527-1	
Flexural strength	10 mm/min	170	MPa	DIN EN ISO 178	
Modulus of elasticity (flexural test)	2 mm/min	3450	MPa	DIN EN ISO 178	
Compression strength	10 mm/min	450	MPa	EN ISO 604	
Compression strength	10mm/min, 10% strain	190	MPa	EN ISO 604	
Compression modulus	1 mm/min	3647	MPa	EN ISO 604	
Compressive strain at break	10 mm/min	45	%	EN ISO 604	
Impact strength (Charpy)	max 7.5 J	75.8	kJ/m ²	DIN EN ISO 179-1	1)
Notched impact strength (Charpy)	max 7.5 J	5	kJ/m ²	DIN EN ISO 179-1	2)
Shore hardness	Shore D	90		DIN EN ISO 868	
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		383	°C	-	1)
Heat distortion temperature	1.85 MPa	368	°C	DIN 53 461	(1) DMA, maximum loss factor tan d (2) Thermal expansion XY/Z axis
Thermal expansion (CLTE)	50-200°C	4.3 / 4.3	10 ⁻⁵ K ⁻¹	DIN 53 752	2)
Thermal expansion (CLTE)	200-300°C	5.3 / 5.3	10 ⁻⁵ K ⁻¹	DIN 53 752	3)
Specific heat		1.04	J/(g*K)	-	
Thermal conductivity	40°C	0.22	W/(K*m)	ISO 8302	
Electrical properties	parameter	value	unit	norm	comment
surface resistivity	23°C	> 10 ¹⁵	Ω	DIN IEC 60093	
volume resistivity	23°C	> 10 ¹⁵	Ω*cm	DIN IEC 60093	
Electric strength DC	23°C	> 35	kV*mm ⁻¹	ISO 60243-1	
Dielectric loss factor	50 Hz	2.2*10 ⁻²		DIN 53483-1	
Dielectric loss factor	1 kHz	2.5*10 ⁻³		DIN 53483-1	
Dielectric loss factor	1 MHz	1.5*10 ⁻²		DIN 53483-1	
Dielectric constant	50 Hz	3.8		DIN 53483-1	
Dielectric constant	1 kHz	3.9		DIN 53483-1	
Dielectric constant	1 MHz	3.7		DIN 53483-1	
Other properties	parameter	value	unit	norm	comment
Water absorption	24 h in water, 23°C	1.3	%	DIN EN ISO 62	(1) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Water absorption	24 h in water, 80°C	3.8	%	DIN EN ISO 62	
Outgassing in high vacuum		passed		ECSS-Q-70-02	
Flammability (UL94)	corresponding to	V0		DIN IEC 60695-11-10;	1)

→ TECASINT 1000 series show significant water uptake. Parts have to be pre-dried before fast heating to above 200 °C (drying process: 2 h per 3 mm wall thickness at 150 °C).

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.