

TECAFLON PTFE natural - 型材 (棒材, 板材, 管件)

化學命名

PTFE (聚四氟乙烯)

顏色

白色 不透明

密度

2.15 g/cm³

主要特色

- 優異的耐化學性
- 固有的防火性
- 連續使用溫度至 260 °C
- 良好的耐候和耐UV性
- 優異的電氣絕緣
- 優異的滑動和耐磨特性

目標產業

- 航空與航太科技
- 化學技術
- 冷凍技術
- 食品科技
- 機械工程
- 半導體科技

機械特性	參數	值	單位	標準	註解
抗拉強度		22	MPa	ASTM D 4894	1)
斷裂伸長率		220	%	ASTM D 4894	2)
壓縮強度	1% strain	5	MPa	ASTM D 695	
蕭氏硬度	D	59		DIN EN ISO 868	
熱特性	參數	值	單位	標準	註解
玻璃轉化溫度		- 20	°C	DIN EN ISO 11357	1)
使用溫度	short term	260	°C	-	2)
使用溫度	long term	260	°C	-	
熱膨脹 (CLTE)	23-100°C, long.	13	10 ⁻⁵ K ⁻¹	ASTM D 696	
導熱係數		0.20	W/(K*m)	ASTM C 177	
電性特性	參數	值	單位	標準	註解
表面電阻		10 ¹⁶	Ω	ASTM D 257	1)
體積電阻		10 ¹⁷	Ω*cm	ASTM D 257	
介電強度	In air, 0.125mm thick	80	kV/mm	ASTM D 149	
介電常數	50-109Hz	2.1		ASTM D 150	
其他特性	參數	值	單位	標準	註解
吸水率	23°C	< 0.01	%	ASTM D 570	
耐燃性(UL94)	corresponding to	V0		DIN IEC 60695-11-10;	1)

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.