TECAPET white - Stock Shapes (rods, plates, tubes)

Chemical Designation
PET (Polyethylene terephthalate)

Colour
white

Density
1.38 g/cm^3

Main features
- very good chemical resistance
- resistent to cleaning agents
- excellent wear properties
- excellent strength and stiffness
- low moisture absorption
- improved surface hardness
- resistance against high energy radiation

Target Industries
- food engineering
- food processing
- engineering for beverage filling systems
- packaging and paper machinery
- semiconductor technology
- printing machines
- mechanical engineering
- pharmaceutical industry

Mechanical properties	condition	value	unit	test method		comment
Modulus of elasticity (tensile test)		470,000	psi	ASTM D 638		(1) Injection molded specimen (2) Injection molded specimen (3) Injection molded specimen
Tensile strength at yield	@ 73 °F	10,000	psi	ASTM D 638		
Elongation at yield (tensile test)	@ 73 °F	4	%	ASTM D 638		
Elongation at break (tensile test)	@ 73 °F	12	%	ASTM D 638		
Flexural strength	@ 73 °F	15,500	psi	ASTM D 790		
Modulus of elasticity (flexural test)	@ 73 °F	470,000	psi	ASTM D 790		
Compression strength	@ 73 °F 1% strain	3,600	psi	ASTM D 695		
Compression strength	@ 73 °F 10% strain	14,000	psi	ASTM D 695		
Compression modulus	@ 73 °F	345,000	psi	ASTM D 695		
Impact strength (Izod)	@ 73 °F	0.53	ft-lbs/in	ASTM D 256		
Rockwell hardness	@ 73 °F, M scale	93		ASTM D 785		
Rockwell hardness	@ 73 °F, R scale	125		ASTM D 785		
Coefficient of friction	Dynamic, 40 psi, 50 fpm	0.25	%	ASTM D 3702	1)	
Coefficient of friction	Static	0.19	%	ASTM D 3702	2)	
Wear rate	Against Steel, 40 psi, 50 fpm	210*10^{-10}	in³-min/ft-lbs-hr	ASTM D 3702	3)	

Thermal properties	condition	value	unit	test method		comment
Melting temperature		490	°F	-	1)	(1) Per ASTM D3418 (2) Data obtained from public source
Heat distortion temperature	@264 psi	175	°F	ASTM D 648		
Heat distortion temperature	@ 66 psi	240	°F	ASTM D 648		
Service temperature	Long Term	230	°F	-		
Service temperature	Intermittent	320	°F	-		
Thermal expansion (CLTE)		3.9	*10^{-5} in/in/°F	ASTM D 696	2)	
Specific heat		0.28	BTU/lb-F°	-		
Thermal conductivity		2.01	BTU-in/hr-ft^2-°F	-		

Electrical properties	condition	value	unit	test method		comment
volume resistance		10^{15}	Ω*cm	ASTM D 257	1)	(1) Injection molded specimen (2) Injection molded specimen (3) Injection molded specimen (4) Injection molded specimen
Dielectric strength		400	V/mil	ASTM D 149	2)	
Dissipation factor	@ 60 Hz, 73 °F	0.02	%	ASTM D 150	3)	
Dielectric constant	@ 60 Hz, 73 °F, 50% RH	3.4	%	ASTM D 150	4)	

Other properties	condition	value	unit	test method	comment
Moisture absorption	@ 24 hrs, 73 °F	0.04	%	ASTM D 570	
Moisture absorption	@ saturation, 73 °F	0.50	%	ASTM D 570	
Flammability (UL94)	3.00 mm Horizontal burn; Thckns: 3.25mm	HB		-	

- Resin specification:
  ASTM D5927-17 TPES0211
  Shapes specification:
  ASTM D 6261-14 S-TPES021012234000

Information about products and services sold by Ensinger, including without limitation information contained in this document do not constitute a warranty by Ensinger as to the quality and state or durability of products or services, or any guarantee of chemical resistance. Such information reflects the current state of our knowledge and is intended only to assist and advise the recipient. The recipient shall not be entitled to rely on Ensinger provided information and the recipient agrees to evaluate such information, to make an independent decision regarding the suitability of such information, products and services for its application, and only use such products, services and information pursuant to then current good product stewardship principles and all regulatory requirements applicable to the recipient's business. Values are guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. Data sheet values are subject to periodic review and the most recent update can be found at www.ensingerplastics.com

Ensinger Inc. Headquarters 365 Meadowlands Boulevard Washington, PA 15301, USA

Phone 800-243-3221 Sales Phone 800-869-4029
Technical Fax 724-746-9209
sales@ensingerusa.com

Date: 2016/10/24

Version: A2