

TECAPET white - Stock Shapes (rods, plates, tubes)

Chemical Designation

PET (Polyethylene terephthalate)

Colour

white

Density

1.38 g/cm³

Main features

- very good chemical resistance
- resistant to cleaning agents
- excellent wear properties
- excellent strength and stiffness
- low moisture absorption
- improved surface hardness
- resistance against high energy radiation

Target Industries

- food engineering
- food processing
- engineering for beverage filling systems
- packaging and paper machinery
- semiconductor technology
- printing machines
- mechanical engineering
- pharmaceutical industry

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>	<i>test method</i>	<i>comment</i>
Modulus of elasticity (tensile test)		470,000 psi	ASTM D 638	(1) Injection molded specimen
Tensile strength at yield	@ 73 °F	10,000 psi	ASTM D 638	(2) Injection molded specimen
Elongation at yield (tensile test)	@ 73 °F	4 %	ASTM D 638	(3) Injection molded specimen
Elongation at break (tensile test)	@ 73 °F	12 %	ASTM D 638	
Flexural strength	@ 73 °F	15,500 psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	470,000 psi	ASTM D 790	
Compression strength	@ 73 °F 1% strain	3,600 psi	ASTM D 695	
Compression strength	@ 73 °F 10% strain	14,000 psi	ASTM D 695	
Compression modulus	@ 73 °F	345,000 psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	0.53 ft-lbs/in	ASTM D 256	
Rockwell hardness	@ 73 °F, M scale	93	ASTM D 785	
Rockwell hardness	@ 73 °F, R scale	125	ASTM D 785	
Coefficient of friction	Dynamic, 40 psi, 50 fpm	0.25 %	ASTM D 3702	1)
Coefficient of friction	Static	0.19 %	ASTM D 3702	2)
Wear rate	Against Steel, 40 psi, 50 fpm	210*10 ⁻¹⁰ in ³ -min/ft-lbs-hr	ASTM D 3702	3)
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>	<i>test method</i>	<i>comment</i>
Melting temperature		490 °F	-	1) (1) Per ASTM D3418
Heat distortion temperature	@264 psi	175 °F	ASTM D 648	(2) Data obtained from public source
Heat distortion temperature	@ 66 psi	240 °F	ASTM D 648	
Service temperature	Long Term	230 °F	-	
Service temperature	Intermittent	320 °F	-	
Thermal expansion (CLTE)		3.9 *10 ⁻⁵ in/in/°F	ASTM D 696	2)
Specific heat		0.28 BTU/lb-F°	-	
Thermal conductivity		2.01 BTU-in/hr-ft ² -°F	-	
<i>Electrical properties</i>	<i>condition</i>	<i>value</i>	<i>test method</i>	<i>comment</i>
Volume resistivity		10 ¹⁵ Ω*cm	ASTM D 257	1) (1) Injection molded specimen
Dielectric strength		400 V/mil	ASTM D 149	2) (2) Injection molded specimen
Dissipation factor	@ 60 Hz, 73 °F	0.02 %	ASTM D 150	3) (3) Injection molded specimen
Dielectric constant	@ 60 Hz, 73 °F, 50% RH	3.4 %	ASTM D 150	4) (4) Injection molded specimen
<i>Other properties</i>	<i>condition</i>	<i>value</i>	<i>test method</i>	<i>comment</i>
Moisture absorption	@ 24 hrs, 73 °F	0.04 %	ASTM D 570	
Moisture absorption	@ saturation, 73 °F	0.50 %	ASTM D 570	

→ Resin specification:
ASTM D6261-10 S-TPES02101220000
Shapes specification:
ASTM D 6261-14 S-TPES021012234000

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.