

TECAFORM® AH FG blue - Stock Shapes (rods, plates, tubes)

Chemical Designation

POM-C (Polyacetal (Copolymer))

Colour

blue

Density

1.41 g/cm³

Main features

- food grade blue
- low moisture absorption
- easily machinable to tight tolerance
- good mechanical properties
- good wear properties
- porosity free

Target Industries

- food processing
- food technology
- food engineering
- packaging and paper machinery
- conveyor technology
- engineering for beverage filling systems
- pharmaceutical industry

Mechanical properties	condition	value		test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	250,000	psi	ASTM D 638	(1) Data obtained from public source
Tensile strength at yield	@ 73 °F	8,800	psi	ASTM D 638	(2) Data obtained from public source
Tensile strength at break	@ 73 °F	9,700	psi	ASTM D 638	(3) Data obtained from public source
Elongation at yield (tensile test)	@ 73 °F	9	%	ASTM D 638	(4) Injection molded data
Elongation at break (tensile test)	@ 73 °F	25	%	ASTM D 638	(5) Injection molded data
Flexural strength	@ 73 °F	12,000	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	400,000	psi	ASTM D 790	
Compression strength	@ 73 °F, 1% strain	1,200	psi	ASTM D 695	
Compression strength	@ 73 °F, 10% strain	11,500	psi	ASTM D 695	(3)
Impact strength (Izod)	@ 73 °F	1.1	ft-lbs/in	ASTM D 256	
Rockwell hardness	M Scale	86		ASTM D 785	
Coefficient of friction	Dynamic, 40 psi, 50 fpm	0.21	%	ASTM D 3702	(4)
Wear rate	Against Steel, 40 psi, 50 fpm	65*10 ⁻¹⁰	in ³ -min/ft-lbs-hr	ASTM D 3702	(5)
Thermal properties	condition	value		test method	comment
Melting temperature		329	°F	-	(1)
Deflection temperature	@ 66 psi	316	°F	ASTM D 648	(2)
Deflection temperature	@264 psi	230	°F	ASTM D 648	(3)
Service temperature	Intermittent	285	°F	-	(4)
Service temperature	Long Term	195	°F	-	(5)
Thermal expansion (CLTE)		4.7*10 ⁻⁵	in/in/°F	ASTM D 696	(6)
Electrical properties	condition	value		test method	comment
Volume resistivity		1.0*10 ⁻¹⁴	Ω/square	ASTM D 257	(1)
Dielectric strength		500	V/mil	ASTM D 149	(2)
Dissipation factor	@ 60HZ, 73°F	0.001		-	(3)
Dielectric loss factor	@60 Hz, 70°	0.001		ASTM D 150	(4)
Dielectric constant	@ 60HZ, 73°F, 50% RH	3.7		ASTM D 150	(5)
Other properties	condition	value		test method	comment
Moisture absorption	@ 24 hrs, 73 °F	0.22	%	ASTM D 570	
Moisture absorption	@ saturation, 73 °F	0.8	%	ASTM D 570	

→ Resin specification:
ASTM D6778-06 POM0211 superseding ASTM D4181-00 POM211
Shapes specification:
ASTM D6100-11 S-POM211

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.