TECAST® T black - Stock Shapes (rods, plates, tubes)

Chemical Designation
PA 6 (Polyamide 6)

Colour
black

Density
1.15 g/cm^3

Main features
- good wear properties
- good mechanical properties
- high fatigue strength
- good damping
- high mechanical load capacity
- resistant to many oils, greases and fuels

Target Industries
- construction industry
- gear manufacturing
- oil and gas industry
- conveyor technology
- agricultural machinery
- heavy duty industry
- mining industry

Mechanical properties	condition	value	unit	test method		comment
Modulus of elasticity (tensile test)	@ 73 °F	350,000	psi	ASTM D 638		(1) Data obtained from public source (2) Data obtained from public source
Tensile strength at yield	@ 73 °F	12,000	psi	ASTM D 638		
Elongation at break (tensile test)	@ 73 °F	30	%	ASTM D 638		
Flexural strength	@ 73 °F	12,000	psi	ASTM D 790		
Modulus of elasticity (flexural test)	@ 73 °F	350,000	psi	ASTM D 790		
Compression strength	@ 1% strain	3,300	psi	ASTM D 695		
Compression strength	@ 10% strain	14,000	psi	ASTM D 695		
Compression modulus		350,000	psi	ASTM D 695		
Impact strength (Izod)	@ 73 °F	1.20	ft-lbs/in	ASTM D 256		
Rockwell hardness	@ 73 °F R Scale	120		ASTM D 785		
Coefficient of friction	Dynamic, 40 psi, 50 fpm	0.26		ASTM D 3702	1)	
Wear (K) factor	Against Steel, 40 psi, 50 fpm	200*10^{-10}	in³-min/ft-lbs-hr	ASTM D 3702	2)	

Thermal properties	condition	value	unit	test method		comment
Melting temperature		428	°F	ASTM D 2133		(1) Data obtained from public source (2) Data obtained from public source
Deflection temperature	@ 66 psi	370	°F	ASTM D 648	1)	
Deflection temperature	@264 psi	200	°F	ASTM D 648	2)	
Service temperature	Intermittent	300	°F	-		
Service temperature	Long Term	200	°F	-		
Thermal expansion (CLTE)		4.0*10^{-5}	in/in/°F	ASTM D 696		
Specific heat		0.40	BTU/lb-F°	-		
Thermal conductivity		1.67	BTU-in/hr-ft^2-°F	-		

Electrical properties	condition	value	unit	test method		comment
surface resistivity		10^{14}	Ω/square	ASTM D 257		
Dielectric strength		500	V/mil	ASTM D 149		
Dielectric constant	@ 60 Hz, 73 °F, 50% RH	3.7		ASTM D 150		

Other properties	condition	value	unit	test method		comment
Moisture absorption	@ 24 hrs, 73 °F	1.2	%	ASTM D 570		(1) estimated
Flammability (UL94)		HB		-	1)	

- Resin specification:
  none
  Shapes specification:
  ASTM D5989-18 S-PA0211

Information about products and services sold by Ensinger, including without limitation information contained in this document do not constitute a warranty by Ensinger as to the quality and state or durability of products or services, or any guarantee of chemical resistance. Such information reflects the current state of our knowledge and is intended only to assist and advise the recipient. The recipient shall not be entitled to rely on Ensinger provided information and the recipient agrees to evaluate such information, to make an independent decision regarding the suitability of such information, products and services for its application, and only use such products, services and information pursuant to then current good product stewardship principles and all regulatory requirements applicable to the recipient's business. Values are guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. Data sheet values are subject to periodic review and the most recent update can be found at www.ensingerplastics.com

Ensinger Inc. Headquarters 365 Meadowlands Boulevard Washington, PA 15301, USA
Phone 800-243-3221 Sales Phone 800-869-4029
Technical Fax 724-746-9209
sales@ensingerusa.com
Date: 2018/12/07
Version: A1