

## TECAPRO® MT white - Stock Shapes (rods, plates, tubes)

### Chemical Designation

PP (Polypropylene)

### Colour

white

### Density

0.92 g/cm<sup>3</sup>

### Main features

- heat stabilized
- autoclavable
- biocompatible
- good chemical resistance
- hydrolysis and superheated steam resistant
- low moisture absorption
- good slide and wear properties

### Target Industries

- medical technology
- pharmaceutical industry
- food engineering

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Modulus of elasticity (tensile test)		273000	psi	ASTM D 638	
Tensile strength at yield	@ 73 °F	5040	psi	ASTM D 638	
Elongation at break (tensile test)	@ 73 °F	50	%	ASTM D 638	
Flexural strength	@ 73 °F	6940	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	271000	psi	ASTM D 790	
Compression strength	1% Sec. @ 73 °F	2600	psi	ASTM D 695	
Compression modulus		232000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	1.0	ft-lbs/in	ASTM D 256	
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Melting temperature		325	°F	-	1) (1) per ASTM D789
Deflection temperature	@264 psi	187	°F	ASTM D 648	
Service temperature	Long Term	212	°F	-	
Service temperature	Intermittent	284	°F	-	
<i>Other properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Moisture absorption	@73 F, 24 hrs	0.03	%	ASTM D 570	

- Resin specification:  
ASTM D4101
- Shapes specification:  
none

Information about products and services sold by Ensinger, including without limitation information contained in this document do not constitute a warranty by Ensinger as to the quality and state or durability of products or services, or any guarantee of chemical resistance. Such information reflects the current state of our knowledge and is intended only to assist and advise the recipient. The recipient shall not be entitled to rely on Ensinger provided information and the recipient agrees to evaluate such information, to make an independent decision regarding the suitability of such information, products and services for its application, and only use such products, services and information pursuant to their current good product stewardship principles and all regulatory requirements applicable to the recipient's business. Values are guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. Data sheet values are subject to periodic review and the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com)