

## TECAMID® 66 IE natural (ST 801) - Stock Shapes (rods, plates, tubes)

### Chemical Designation

PA 66 (Polyamide 66)

### Colour

natural opaque

### Density

1.08 g/cm<sup>3</sup>

### Main features

- high toughness
- excellent impact strength
- good wear resistance
- good mechanical properties

### Target Industries

- conveyor technology
- gear manufacturing
- heavy duty industry
- mechanical engineering

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	245,000	psi	ASTM D 638	(1) Data from public source (2) Data from public source
Tensile strength at yield	@ 73 °F	6,600	psi	ASTM D 638	
Elongation at break (tensile test)	@ 73 °F	38	%	ASTM D 638	
Flexural strength	@ 73 °F	7,900	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	245,000	psi	ASTM D 790	
Compression strength	@ 1% strain	2,250	psi	ASTM D 695	
Compression strength	@ 10% strain	8,100	psi	ASTM D 695	
Compression modulus		200,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	3.17	ft-lbs/in	ASTM D 256	
Rockwell hardness	R Scale	97		ASTM D 785	
Coefficient of friction	Dynamic, 40 psi, 50 fpm	0.28		ASTM D 3702	1)
Wear (K) factor	Against Steel, 40 psi, 50 fpm	200*10 <sup>-10</sup>	in <sup>3</sup> -min/ft-lbs-hr	ASTM D 3702	2)
Thermal properties	condition	value	unit	test method	comment
Melting temperature		504	°F	DIN EN ISO 11357	1) (1) Data from public source
Deflection temperature	@ 66 psi	315	°F	ISO-R 75 Method B	2) (2) Data from public source
Deflection temperature	@264 psi	147	°F	ISO-R 75 Method A	3) (3) Data from public source
Service temperature	Long Term	185	°F	-	4) (4) Data obtained from public source
Thermal expansion (CLTE)	flow 73 - 140 F	6.7*10 <sup>-4</sup>	in/in/°F	ASTM E 831	5) (5) Data from public source
Other properties	condition	value	unit	test method	comment
Moisture absorption	@ 24 hrs, 73 °F	0.30	%	ASTM D 570	(1) Data from public source - resin
Moisture absorption	@ saturation, 73 °F	6.7	%	ASTM D 570	1) (2) Data from public source - resin
Flammability (UL94)	0.81 mm thick	HB		-	2)

→ Resin specification:  
ASTM D6779-11 PA0171  
Shapes specification:  
ASTM D5989-11 S-PA0100

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com).