

TECAMID 6 ID blue - 型材(棒材,板材,管件)

化學命名

PA 6 (聚醯胺 6)

顏色

藍灰色 不透明

密度

1.24 g/cm³

添加物

可偵測填充物

主要特色

- 高韌性
- 耐油、潤滑油及燃油
- 電絕緣
- 良好的磨損性
- 良好的可焊接性和黏結性
- 良好的滑動及耐磨特性
- 高強度
- 良好的加工特性

目標產業

- 電子學
- 食品科技
- 機械工程

加工後所產生的數據(依德國標準氣候為主)。

機械特性	參數	值	單位	標準	註解
抗拉強度	50mm/min	80	MPa	DIN EN ISO 527-2	
彈性模數 (張力測試)	1mm/min	3600	MPa	DIN EN ISO 527-2	1)
降伏點抗拉強度	50mm/min	80	MPa	DIN EN ISO 527-2	
降伏點伸長率	50mm/min	4	%	DIN EN ISO 527-2	
斷裂伸長率	50mm/min	21	%	DIN EN ISO 527-2	
衝擊強度(Charpy)	max. 7,5J	n.b.	kJ/m ²	DIN EN ISO 179-1eU	2)
缺口衝擊強度(Charpy)	max. 7,5J	4	kJ/m ²	DIN EN ISO 179-1eA	
蕭氏硬度	D	81		DIN EN ISO 868	
熱特性	參數	值	單位	標準	註解
玻璃轉化溫度		45	°C	DIN EN ISO 11357	1)
熔化溫度		220	°C	DIN EN ISO 11357	
使用溫度	short term	160	°C		2)
使用溫度	long term	100	°C		
電性特性	參數	值	單位	標準	註解
表面電阻	Silver electrode, 23°C, 12% r.h.	> 10 ¹³	Ω	-	1)
					(1) Specimen in 20mm thickness
其他特性	參數	值	單位	標準	註解
吸水率	24h / 96h (23°C)	0.3 / 0.6	%	DIN EN ISO 62	1)
耐熱水/鹼	(+)	-			2)
耐候性	-	-			3)
耐燃性(UL94)	corresponding to	HB		DIN IEC 60695-11-10;	4)
					(1) Ø ca. 50mm, h=13mm (2) (+) limited resistance (3) - poor resistance (4) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.