TECASON P MT brown - Stock Shapes (rods, plates, tubes)

Chemical Designation
PPSU (Polyphenylsulfone)

Colour
brown opaque

Density
1.31 g/cm^3

Main features
- high thermal and mechanical capacity
- biocompatible
- hydrolysis and superheated steam resistant
- good impact strength
- high stiffness
- high strength
- good chemical resistance
- high gamma radiation resistance

Target Industries
- medical technology
- chemical technology
- food technology
- mechanical engineering
- automotive industry

Mechanical properties	parameter	value	unit	norm		comment
Tensile strength	50mm/min	81	MPa	DIN EN ISO 527-2		(1) For tensile test: specimen type 1b (2) For flexural test: support span 64mm, norm specimen. (3) Specimen 10x10x10mm (4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression. (5) For Charpy test: support span 64mm, norm specimen. n.b. = not broken (6) Specimen in 4mm thickness
Modulus of elasticity (tensile test)	1mm/min	2300	MPa	DIN EN ISO 527-2	1)	
Tensile strength at yield	50mm/min	81	MPa	DIN EN ISO 527-2		
Elongation at yield (tensile test)	50mm/min	7	%	DIN EN ISO 527-2		
Elongation at break (tensile test)	50mm/min	> 50	%	DIN EN ISO 527-2		
Flexural strength	2mm/min, 10 N	107	MPa	DIN EN ISO 178	2)	
Modulus of elasticity (flexural test)	2mm/min, 10 N	2300	MPa	DIN EN ISO 178		
Compression strength	1% / 2% 5mm/min, 10 N	18 / 30	MPa	EN ISO 604	3)	
Compression modulus	5mm/min, 10 N	2000	MPa	EN ISO 604	4)	
Impact strength (Charpy)	max. 7,5J	n.b.	kJ/m^2	DIN EN ISO 179-1eU	5)	
Notched impact strength (Charpy)	max. 7,5J	13	kJ/m^2	DIN EN ISO 179-1eA		
Ball indentation hardness		143	MPa	ISO 2039-1	6)	

Thermal properties	parameter	value	unit	norm		comment
Glass transition temperature		218	°C	DIN EN ISO 11357	1)	(1) Found in public sources. (2) n.a. = not applicable (3) Found in public sources. Individual testing regarding application conditions is mandatory.
Melting temperature		n.a.	°C	DIN EN ISO 11357	2)	
Service temperature	short term	190	°C	-	3)	
Service temperature	long term	170	°C	-		
Thermal expansion (CLTE)	23-60°C, long.	6	10^{-5} K^{-1}	DIN EN ISO 11359-1;2		
Thermal expansion (CLTE)	23-100°C, long.	6	10^{-5} K^{-1}	DIN EN ISO 11359-1;2		
Specific heat		1.1	J/(g*K)	ISO 22007-4:2008		
Thermal conductivity		0.25	W/(K*m)	ISO 22007-4:2008		

Electrical properties	parameter	value	unit	norm		comment
surface resistivity	Silver electrode, 23°C, 12% r.h.	10^{14}	Ω	-	1)	(1) Specimen in 20mm thickness (2) Due to the brown colourant and moisture uptake of the material the electrical insulation properties cannot be 100% guaranteed, despite single measurements suggesting otherwise.
volume resistivity	Silver electrode, 23°C, 12% r.h.	10^{14}	Ω*cm	-	2)	

Other properties	parameter	value	unit	norm		comment
Water absorption	24h / 96h (23°C)	0.1 / 0.2	%	DIN EN ISO 62	1)	(1) Ø ca. 50mm, h=13mm (2) + good resistance (3) (+) limited resistance
Resistance to hot water/ bases		+		-	2)	
Resistance to weathering		(+)		-	3)	
Flammability (UL94)	listed (value at 0.79mm)	V0		DIN IEC 60695-11-10;		

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.

Manufactured by: Ensinger Group, a German based plastic manufacturer

Represented by: Ensinger Asia Holding Pte Ltd. (Singapore Branch) for Asia Pacific other than Japan+China

63 Hillview Avenue #02-03
Lam Soon Industrial Building
Singapore 669569
Tel +65 65524177
Fax +65 65525177
www.ensingerplastics.com/en-sg/

Date: 2017/03/30

Version: AB