

## TECAFLON PVDF ELS black - 型材 (棒材, 板材, 管件)

### 化學命名

PVDF (聚二氟亞乙烯)

### 顏色

黑色

### 密度

1.78 g/cm<sup>3</sup>

### 添加物

黑色導電性碳

### 主要特色

- 導電性
- 優異的耐化學性
- 固有的防火性
- 連續使用溫度至150 °C
- 良好的滑動及耐磨特性
- 優異的耐候和耐UV性
- 優異的可焊接性

### 目標產業

- 化學技術
- 電子學
- 能源工業
- 機械工程

機械特性	參數	值	單位	標準	註解
彈性模數 (張力測試)	1mm/min	3100	MPa	DIN EN ISO 527-2	1)
降伏點抗拉強度	50mm/min	55	MPa	DIN EN ISO 527-2	
降伏點伸長率	50mm/min	4	%	DIN EN ISO 527-1	
斷裂伸長率	50mm/min	8	%	DIN EN ISO 527-2	
衝擊強度(Charpy)	max. 7,5J	67	kJ/m <sup>2</sup>	DIN EN ISO 179-1	2)
球壓式硬度		162	MPa	ISO 2039-1	3)
熱特性	參數	值	單位	標準	註解
玻璃轉化溫度		-40	°C	DIN EN ISO 11357	1)
熔化溫度		177	°C	DIN EN ISO 11357	
使用溫度	short term	150	°C	-	2)
使用溫度	long term	150	°C	-	
電性特性	參數	值	單位	標準	註解
表面電阻		10 <sup>2</sup> - 10 <sup>6</sup>	Ω	DIN EN 61340-2-3	
其他特性	參數	值	單位	標準	註解
耐熱水/鹼		+	-	-	1)
耐候性		+	-	-	2)

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com). Technical changes reserved.