

TECAPEEK MT XRO green - 型材 (棒材, 板材, 管件)

化學命名

PEEK (聚醚醚酮)

顏色

綠色 不透明

密度

1.38 g/cm³

添加物

硫酸銀

主要特色

- 高蠕變抗性
- x光線下可見
- 良好的耐化學性
- 良好的滑動及耐磨特性
- 高能輻射抗性
- 優異的耐應力破裂
- 耐水解和熱蒸氣
- 非常易於消毒

目標產業

- 醫療科技
- 機械工程
- 食品工程

機械特性	參數	值	單位	標準	註解
抗拉強度	50mm/min	117	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
彈性模數 (張力測試)	1mm/min	4400	MPa	DIN EN ISO 527-2	(1) (2) For Charpy test: support span 64mm, norm specimen. n.b. = not broken
斷裂伸長率	50mm/min	11	%	DIN EN ISO 527-2	
衝擊強度(Charpy)	max. 7,5J	n.b.	kJ/m ²	DIN EN ISO 179-1eU	2)
缺口衝擊強度(Charpy)	max. 7,5J	5.6	kJ/m ²	DIN EN ISO 179-1eA	
熱特性	參數	值	單位	標準	註解
熔化溫度		343	°C	DIN 53765	(1) Found in public sources. Individual testing regarding application conditions is mandatory.
使用溫度	short term	300	°C	-	1)
使用溫度	long term	260	°C	-	

→ TECAPEEK 產品是使用 Victrex® PEEK 原物料製作而成。

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on extruded and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.