

TECAFORM® AH black - Stock Shapes (rods, plates, tubes)

Chemical Designation

POM-C (Polyacetal (Copolymer))

Colour

white black

Density

1.41 g/cm³

Main features

- porosity free
- good wear properties
- low water absorption
- good chemical resistance
- easy to machine
- high dimensional stability

Target Industries

- construction industry
- agricultural machinery
- automotive industry
- food engineering
- conveyor technology
- gear manufacturing
- heavy duty industry
- packaging and paper machinery
- process engineering

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	330,000	psi	ASTM D 638	(1) Data obtained from public source
Tensile strength at yield	@ 73 °F	9,300	psi	ASTM D 638	
Elongation at yield (tensile test)	@ 73 °F	9	%	ASTM D 638	1)
Elongation at break (tensile test)	@ 73 °F	40	%	ASTM D 638	
Flexural strength	@ 73 °F	13,000	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	400,000	psi	ASTM D 790	
Compression strength	@ 73 °F, 5 % strain	4,500	psi	ASTM D 695	
Compression strength	@ 73 °F, 1% strain	2,500	psi	ASTM D 695	
Compression strength	@ 73 °F, 10% strain	12,000	psi	ASTM D 695	
Compression modulus	@ 73 °F	250,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	1.0	ft-lbs/in	-	
Rockwell hardness	@ 73 °F M Scale	86		ASTM D 785	
Rockwell hardness	@ 73 °F, R scale	120		ASTM D 785	
Coefficient of friction	Dynamic 40 psi, 50 fpm	.21		ASTM D 3702	
Wear rate	40 psi, 50 fpm	65 x 10 ⁻¹⁰	in ³ -min/ft-lbs-hr	ASTM D 3702	
Thermal properties	condition	value	unit	test method	comment
Melting temperature		329	°F	-	(1) per UL746B
Deflection temperature	@ 66 psi	316	°F	ASTM D 648	
Deflection temperature	@ 264 psi	230	°F	ASTM D 648	
Service temperature	Intermittent	285	°F	-	
Service temperature	Long Term	195	°F	-	1)
Thermal expansion (CLTE)		4.7*10 ⁻⁵	in/in/°F	ASTM D 696	
Electrical properties	condition	value	unit	test method	comment
volume resistance		1.0 x 10 ¹⁴	Ω*cm	ASTM D 257	
Dielectric strength		500	V/mil	ASTM D 149	
Dissipation factor	@ 60 Hz, 73 °F	.001	%	ASTM D 150	
Dielectric constant	@ 60 Hz, 73 °F, 50% RH	3.7	%	ASTM D 150	
Other properties	condition	value	unit	test method	comment
Moisture absorption	@ 24 hrs, 73 °F	0.18	%	ASTM D 570	(1) at 1.5mm thickness injection molded sample
Moisture absorption	@ saturation, 73 °F	.80	%	ASTM D 570	
Flammability (UL94)	UL 94	HB	%	-	1)

→ Resin specification:
ASTM D6778-06 POM0211 superseding ASTM D4181-00 POM211
Shapes specification:
ASTM D6100-11 S-POM211

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.