

Celcon® M-25 blue (TECAFORM® AH MT) - Stock Shapes (rods, plates, tubes)

Chemical Designation

POM-C (Polyacetal (Copolymer))

Colour

blue

Density

1.41 g/cm³

Main features

- meets requirements for USP Class VI
- compliant with cytotoxicity according to ISO 10993-5
- good machinability

Target Industries

- medical technology
- pharmaceutical industry

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)		390,000	psi	ASTM D 638	(1) Data obtained from public source
Tensile strength at yield		9,400	psi	ASTM D 638	
Tensile strength at break	@ 73 °F	10,000	psi	ASTM D 638	1)
Elongation at yield (tensile test)		10	%	ASTM D 638	
Elongation at break (tensile test)		28	%	ASTM D 638	
Flexural strength		13,400	psi	ASTM D 790	
Modulus of elasticity (flexural test)		411,000	psi	ASTM D 790	
Compression strength	@ 73 °F, 1% strain	2,900	psi	ASTM D 695	
Compression strength	@ 73 °F, 10% strain	13,500	psi	ASTM D 695	
Compression modulus	@ 73 °F	273,600	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	.85	ft-lbs/in	ASTM D 256	
Thermal properties	condition	value	unit	test method	comment
Melting temperature		320	°F	-	1) (1) per ASTM D3418
Deflection temperature	@264 psi	230	°F	ASTM D 648	2) (2) Data obtained from public source
Service temperature	Long Term	212	°F	-	3) (3) Data obtained from public source
Service temperature	short term	284	°F	-	3) (4) data obtained from public source
Thermal expansion (CLTE)	@ 73°F to 131°F	5.5*10 ⁻⁵	in/in/°F	ASTM E 831	4)
Electrical properties	condition	value	unit	test method	comment
surface resistivity		10 ¹⁴	Ω/square	DIN IEC 60093	1) (1) data obtained from public sources
volume resistance		10 ¹⁴	Ω*cm	DIN IEC 60093	2) (2) data obtained from public sources
Dielectric loss factor		0.003		DIN IEC 60250	3) (3) data obtained from public sources
Dielectric constant	@ 10 ³ Hz	3.5		DIN IEC 60250	4) (4) data obtained from public sources
Other properties	condition	value	unit	test method	comment
Moisture absorption	@ 24 hrs.	0.12	%	ASTM D 570	

→ Resin specification:
ASTM D6778-14 POM0210B55340
Shapes specification:
ASTM D6100-11 S-POM0211

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters
365 Meadowlands Boulevard
Washington, PA 15301, USA

Phone 800-243-3221 Sales
Phone 800-869-4029 Technical
Fax 724-746-9209
sales@ensingerusa.com

Date: 2017/08/07

Version: A0