

## TECAST® L black - Stock Shapes (rods, plates, tubes)

### Chemical Designation

PA 6 (Polyamide 6)

### Colour

black

### Density

1.14 g/cm<sup>3</sup>

### Fillers

oil

### Main features

- excellent wear properties
- excellent strength and stiffness
- high mechanical load capacity
- very good slide and wear properties

### Target Industries

- construction industry
- agricultural machinery
- gear manufacturing
- mining industry
- conveyor technology
- oil and gas industry

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Tensile strength	@ 73 °F	9,000	psi	ASTM D 638	(1) Data obtained from public source
Modulus of elasticity (tensile test)	@ 73 °F	350,000	psi	ASTM D 638	(2) Data obtained from public source
Tensile strength at break	@ 73 °F	10,000	psi	ASTM D 638	1)
Elongation at yield (tensile test)	@ 73 °F	8	%	ASTM D 638	2)
Elongation at break (tensile test)	@ 73 °F	25	%	ASTM D 638	
Flexural strength	@ 73 °F	12,500	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	350,000	psi	ASTM D 790	
Impact strength (Izod)	@ 73 °F	1.2	ft-lbs/in	ASTM D 256	
Rockwell hardness	@ 73 °F	100		ASTM D 785	
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Melting temperature		428	°F	ASTM D 2133	(1) Data obtained from public source
Service temperature	Intermittent	330	°F	-	(2) Data obtained from public source
Service temperature	Long Term	200	°F	-	(3) Data obtained from public source
Thermal expansion (CLTE)		4.0*10 <sup>-5</sup>	in/in/°F	ASTM D 696	1)
Specific heat		0.73	BTU/lb-F°	-	2)
Thermal conductivity		2.57	BTU-in/hr-ft <sup>2</sup> -°F	-	3)
<i>Electrical properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
surface resistivity		1.0*10 <sup>14</sup>	Ω/square	ASTM D 257	1) (1) Data obtained from public source
volume resistivity		1.0*10 <sup>14</sup>	Ω*cm	ASTM D 257	2) (2) Data obtained from public source
<i>Other properties</i>	<i>condition</i>	<i>value</i>	<i>unit</i>	<i>test method</i>	<i>comment</i>
Moisture absorption	@ 24 hrs, 73 °F	0.75	%	ASTM D 570	(1) Data obtained from public source
Flammability (UL94)		HB	%	-	1)

→ Resin specification:  
none  
Shapes specification:  
ASTM D5989-18 S-PA0251

Information about products and services sold by Ensinger, including without limitation information contained in this document do not constitute a warranty by Ensinger as to the quality and state or durability of products or services, or any guarantee of chemical resistance. Such information reflects the current state of our knowledge and is intended only to assist and advise the recipient. The recipient shall not be entitled to rely on Ensinger provided information and the recipient agrees to evaluate such information, to make an independent decision regarding the suitability of such information, products and services for its application, and only use such products, services and information pursuant to their current good product stewardship principles and all regulatory requirements applicable to the recipient's business. Values are guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. Data sheet values are subject to periodic review and the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com)