

TECAMID 66 GF15 FR black - Stock Shapes (rods, plates, tubes)

Chemical Designation

PA 66 (Polyamide 66)

Colour

black

Density

1.3 g/cm³

Fillers

flame retardant (halogen free), glass fibres

Main features

- resistant to many oils, greases and fuels
- high strength

Target Industries

- aircraft and aerospace interiors
- aircraft and aerospace technology
- mechanical engineering
- transportation

The compound is in the phase of further development. The characteristic values of this product may change.

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	@ 73 °F	465,000	psi	ASTM D 638	
Tensile strength at yield	@ 73 °F	6,890	psi	ASTM D 638	
Elongation at break (tensile test)	@ 73 °F	5.8	%	ASTM D 638	
Flexural strength	@ 73 °F	17,200	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@ 73 °F	722,000	psi	ASTM D 790	
Compression strength	1% / 10% strain	3,900/21,500	psi	ASTM D 695	
Compression modulus		386,000	psi	ASTM D 695	
Impact strength (Izod)	@ 73 °F	0.70	ft-lbs/in	ASTM D 256	
Rockwell hardness	M scale	85		ASTM D 785	
Rockwell hardness	R Scale	118		-	
Thermal properties	condition	value	unit	test method	comment
Melting temperature		487	°F	-	(1) publicly sourced data
Service temperature	Long Term	230	°F	-	(2) publicly sourced data
Service temperature	Intermittent	338	°F	-	
Other properties	condition	value	unit	test method	comment
Flammability	60 seconds Vertical Bunsen Burner test	pass		AITM 2.0002A	1) (1) 4 mm test specimen
Flammability	15 seconds Horizontal Bunsen Burner test	pass		AITM 2.0003	2) (2) 4 mm test specimen
Flammability	Specific Optical Smoke Density	pass		AITM 2.0007B	3) (3) 4 mm test specimen
Flammability	60 seconds Vertical Bunsen Burner test 25.853 (a) Amdt 25-116 App F Part 1(a)(1)(i)	pass		FAR 25.853	4) (4) 3 mm test specimen
Flammability	Gas Toxicity, as Per Airbus directive ABD0031	pass		AITM 3.0005	5) (5) 4 mm test specimen

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

Ensinger Inc. Headquarters
365 Meadowlands Boulevard
Washington, PA 15301, USA

Phone 800-243-3221 Sales
Phone 800-869-4029 Technical
Fax 724-746-9209
sales@ensingerusa.com

Date: 2019/02/28

Version: A1