

TECAMID 66 GF15 FR black - Stock Shapes (rods, plates, tubes)

Chemical Designation

PA 66 (Polyamide 66)

Colour

black

Density

1.3 g/cm³

Fillers

flame retardant (halogen free), glass fibres

Main features

- resistant to many oils, greases and fuels
- high strength

Target Industries

- aircraft and aerospace interiors
- aircraft and aerospace technology
- mechanical engineering
- transportation

The compound is in the phase of further development. The characteristic values of this product may change.

<i>Mechanical properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Modulus of elasticity (tensile test)	@ 73 °F	465,000	psi	ASTMD 638	
Tensile strength at yield	@ 73 °F	6,890	psi	ASTMD 638	
Elongation at break (tensile test)	@ 73 °F	5.8	%	ASTMD 638	
Flexural strength	@ 73 °F	17,200	psi	ASTMD 790	
Modulus of elasticity (flexural test)	@ 73 °F	722,000	psi	ASTMD 790	
Compression strength	1% / 10% strain	3,900/21,500	psi	ASTMD 695	
Compression modulus		386,000	psi	ASTMD 695	
Impact strength (Izod)	@ 73 °F	0.70	ft-lbs/in	ASTMD 256	
Rockwell hardness	R Scale	118		-	
Rockwell hardness	Mscale	85		ASTMD 785	
<i>Thermal properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Melting temperature		487	°F	-	(1) publicly sourced data (2) publicly sourced data
Service temperature	Intermittent	338	°F	-	1)
Service temperature	Long Term	230	°F	-	2)
<i>Other properties</i>	<i>condition</i>	<i>value</i>		<i>test method</i>	<i>comment</i>
Flammability	Specific Optical Smoke Density	pass		AITM 2.0007B	1) (1) 4 mm test specimen (2) 4 mm test specimen
Flammability	Gas Toxicity, as Per Airbus directive ABD0031	pass		AITM 3.0005	2) (3) 4 mm test specimen (4) 3 mm test specimen (5) 4 mm test specimen
Flammability	15 seconds Horizontal Bunsen Burner test	pass		AITM 2.0003	3)
Flammability	60 seconds Vertical Bunsen Burner test 25.853 (a) Amdt 25-116 App F Part 1(a)(1)(i)	pass		FAR 25.853	4)
Flammability	60 seconds Vertical Bunsen Burner test	pass		AITM 2.0002A	5)

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.