

TECAST T blue - Stock Shapes (rods, plates, tubes)

Chemical Designation

PA 6 C (Cast polyamide 6)

Colour

blue opaque

Density

1.15 g/cm³

Data generated directly after machining
(standard climate Germany).

Main features

- good wear properties
- good mechanical properties
- high fatigue strength
- good damping
- high mechanical load capacity
- resistant to many oils, greases and fuels

Target Industries

- construction industry
- gear manufacturing
- oil and gas industry
- conveyor technology
- agricultural machinery
- heavy duty industry
- mining industry

Mechanical properties	parameter	value	unit	norm	comment
Tensile strength	50mm/min	89	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
Modulus of elasticity (tensile test)	1mm/min	3600	MPa	DIN EN ISO 527-2	
Tensile strength at yield	50mm/min	89	MPa	DIN EN ISO 527-2	
Elongation at yield (tensile test)	50mm/min	18	%	DIN EN ISO 527-2	
Elongation at break (tensile test)	50mm/min	25	%	DIN EN ISO 527-2	
Shore hardness	D	82		DIN EN ISO 868	
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		49	°C	DIN EN ISO 11357	(1) Found in public sources. Individual testing regarding application conditions is mandatory. (2) Found in public sources.
Melting temperature		217	°C	DIN EN ISO 11357	
Service temperature	short term	170	°C	-	1)
Service temperature	long term	100	°C	-	
Thermal expansion (CLTE)	23-60°C, long.	11	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	2)
Specific heat		1.6	J/(g*K)	ISO 22007-4:2008	
Thermal conductivity		0.33	W/(K*m)	ISO 22007-4:2008	
Electrical properties	parameter	value	unit	norm	comment
surface resistivity		10 ¹⁴	Ω	DIN IEC 60093	
Other properties	parameter	value	unit	norm	comment
Moisture absorption	24h / 96h (23°C)	0.2 / 0.5	%	DIN EN ISO 62	1)
Resistance to hot water/ bases		(+)		-	2)
Resistance to weathering		(+)		-	
Flammability (UL94)	corresponding to	HB		DIN IEC 60695-11-10;	3)

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions (typically rods with diameter 40-60 mm according to DIN EN 15860) on cast and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.