

## TECAPEEK CM XP96 natural - Stock Shapes (rods, plates, tubes)

### Chemical Designation

PEEK (Polyetheretherketone)

### Colour

beige

### Density

1.34 g/cm<sup>3</sup>

### Main features

- excellent strength
- broad chemical compatibility
- good dimensional stability
- high stiffness

### Target Industries

- oil and gas industry
- chemical and refinery industry

Mechanical properties	condition	value	unit	test method	comment
Modulus of elasticity (tensile test)	@73°F	700,000	psi	ASTM D 638	
Tensile strength at break	@73°F	15,000	psi	ASTM D 638	
Elongation at yield (tensile test)		6.7	%	ASTM D 638	
Elongation at break (tensile test)	@73°F	10	%	ASTM D 638	
Flexural strength	@73°F	25,000	psi	ASTM D 790	
Modulus of elasticity (flexural test)	@73°F	660,000	psi	ASTM D 790	
Compression strength	@73°F, 10% strain	19,300	psi	ASTM D 695	
Compression modulus	@73°F	360,000	psi	ASTM D 695	
Impact strength (Izod)	@73°F, notched	.58	ft-lbs/in	ASTM D 256	
Shore hardness	D Scale	88		ASTM D 2240	
Thermal properties	condition	value	unit	test method	comment
Melting temperature		649	°F	-	
Deflection temperature		300	°F	ASTM D 648	
Service temperature	Short Term	500	°F	-	
Thermal conductivity		1.7	BTU-in/hr-ft <sup>2</sup> -°F	ASTM C 177	
Electrical properties	condition	value	unit	test method	comment
volume resistance		4.9*10 <sup>16</sup>	Ω*cm	ASTM D 257	
Dielectric strength		1900	kV/mm	ASTM D 149	
Other properties	condition	value	unit	test method	comment
Moisture absorption		0.05	%	ASTM D 570	

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com).