

## TECADUR MT TR natural - Stock Shapes (rods, plates, tubes)

### Chemical Designation

PCT-G (Poly Cyclohexylenedimethylene Terephthalate glycol-modified)

### Colour

transparent transparent

### Density

1.18 g/cm<sup>3</sup>

### Main features

- good chemical resistance
- excellent impact strength
- high gamma radiation resistance

### Target Industries

- medical technology
- pharmaceutical industry
- chemical technology

Mechanical properties	parameter	value	unit	norm	comment
Modulus of elasticity (tensile test)	1mm/min	1500	MPa	DIN EN ISO 527-2	1) (1) For tensile test: specimen type 1b
Tensile strength at yield	50mm/min	48	MPa	DIN EN ISO 527-2	(2) For flexural test: support span 64mm, norm specimen.
Elongation at break (tensile test)	50mm/min	181	%	DIN EN ISO 527-2	(3) Specimen 10x10x10mm
Flexural strength	2mm/min, 10 N	63	MPa	DIN EN ISO 178	(4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.
Modulus of elasticity (flexural test)	2mm/min, 10 N	1420	MPa	DIN EN ISO 178	(5) For Charpy test: support span 64mm, norm specimen.
Compression strength	1% / 2% / 5% 5mm/min, 10 N	15/25/50	MPa	EN ISO 604	(6) Specimen in 4mm thickness n.b. = not broken
Compression modulus	5mm/min, 10 N	1020	MPa	EN ISO 604	4)
Impact strength (Charpy)	max. 7,5J	n.b.	kJ/m <sup>2</sup>	DIN EN ISO 179-1eU	5)
Notched impact strength (Charpy)	max. 7,5J	94	kJ/m <sup>2</sup>	DIN EN ISO 179-1eA	
Ball indentation hardness		81	MPa	ISO 2039-1	6)
Thermal properties	parameter	value	unit	norm	comment
Glass transition temperature		108	°C	DIN EN ISO 11357	
Thermal expansion (CLTE)	23-100°C, longitudinal	8	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	23-60°C, longitudinal	8	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
Other properties	parameter	value	unit	norm	comment
Moisture absorption	24h / 96h (23°C)	0.09 / 1.74	%	DIN EN ISO 62	(1) - poor resistance (2) - poor resistance (3) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Resistance to hot water/ bases		-	-	-	1)
Resistance to weathering		-	-	-	2)
Flammability (UL94)	corresponding to	HB	-	-	3)

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com). Technical changes reserved.