

TECANYL VH2 grey - 型材 (棒材, 板材, 管件)

化學命名

PPE (聚苯醚)

顏色

灰色 不透明

密度

1.1 g/cm³

添加物

阻燃劑 (無鹵素)

主要特色

- 根據FAR 25.853 防火測試
- 絕佳的尺寸穩定性
- 優異的耐化學性
- 根據UL94 V-0 耐燃測試
- 低煙排放
- 低吸濕性
- 良好的電絕緣性

目標產業

- 航空與航太內裝
- 航空與航太科技
- 鐵路內裝
- 運輸工具

機械特性	參數	值	單位	標準	註解
抗拉強度	50 mm/min	57	MPa	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
彈性模數 (張力測試)	1mm/min	2300	MPa	DIN EN ISO 527-2	(1) (2) For flexural test: support span 64mm, norm specimen.
降伏點抗拉強度	50mm/min	57	MPa	DIN EN ISO 527-2	(3) Specimen 10x10x10mm
降伏點伸長率	50mm/min	14	%	DIN EN ISO 527-2	(4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression.
斷裂伸長率	50mm/min	22	%	DIN EN ISO 527-2	(5) For Charpy test: support span 64mm, norm specimen.
抗彎強度	2mm/min, 10 N	95	MPa	DIN EN ISO 178	(2) (6) Specimen in 4mm thickness
彈性模數 (彎曲測試)	2mm/min, 10 N	2070	MPa	DIN EN ISO 178	
壓縮強度	1% / 2% / 5%	19/34/78	MPa	EN ISO 604	(3)
壓縮模數	5mm/min	1300	MPa	EN ISO 604	(4)
衝擊強度(Charpy)	max. 7.5J	96	kJ/m ²	DIN EN ISO 179-1eU	(5)
缺口衝擊強度(Charpy)	max. 7.5J	11	kJ/m ²	DIN EN ISO 179-1eA	
球壓式硬度		141	MPa	ISO 2039-1	(6)
熱特性	參數	值	單位	標準	註解
玻璃轉化溫度		151	°C	DIN EN ISO 11357	(1) Found in public sources. Individual testing regarding application conditions is mandatory.
使用溫度	long term	85	°C	-	
使用溫度	short term	110	°C	-	(1)
熱膨脹 (CLTE)	23-60°C, longitudinal	8,1	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
熱膨脹 (CLTE)	23-100°C, longitudinal	8,1	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	
其他特性	參數	值	單位	標準	註解
吸水率	24h / 96h (23°C)	0.09/0.15	%	DIN EN ISO 62	(1) passed, 3 mm specimen
耐燃性	60 sec. Vertical Bunsen Burner test FAR 25.853 Appx F, Prt 1, (a), 1, (Air)	+		FAR 25.853	(1) (2) Units: 1.5 mm
耐燃性(UL94)		V0		-	(2) (3) ASTM Test Method 60695-2
耐燃性	Glow Wire Flammability Index 960°C passes @	1.0	mm	-	(3) (4) ASTM Test Method 60695-2
耐燃性	Glow Wire Ignitability Temp, 1.0 mm	775	°C	-	(4) (5) ASTM Test Method 60695-2
耐燃性	Glow Wire Ignitability Temp, 1.5 mm	775	°C	-	(5) (6) ASTM Test Method 60695-2
耐燃性	Glow Wire Ignitability Temp, 2.0 mm	775	°C	-	(6) (7) ASTM Test Method 60695-2
耐燃性	Glow Wire Ignitability Temp, 3.0 mm	800	°C	-	(7) (8) passed, FAA Smoke Density Test (resin data)
耐燃性	FAR 25.853 Appx F, Prt 1, (a), 1, (Air)	+		FAR 25.853	(8) (9) passed, Toxicity - Draeger Tube (resin data)
耐燃性	FAR 25.853 Appx F, Prt 1, (a), 1, (Air)	+		-	(9) (10) Flame Spread Index
耐燃性	ASTM E 162 (rail)	~15		-	(10) (11) passed, FAR 25.853
耐燃性	ASTM E 662 (Air/Rail) Ds @ 1.5 min	11-13		-	(11) (12) passed, FAR 25.853
耐燃性	ASTM E 662 (Air/Rail) Ds @ 4.0 min	20-40		-	

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.