TECADUR PBT UD blue - Stock Shapes (rods, plates, tubes)

Chemical Designation
PBT (Polybutylene terephthalate)

Colour
blue opaque

Density
1.56 g/cm^3

Fillers
detectable filler

Main features
- resistent to cleaning agents
- good chemical resistance
- food grade blue
- good dimensional stability
- good impact strength
- metal detectable
- x-ray opaque

Target Industries
- food engineering
- food processing
- conveyor technology
- packaging and paper machinery

Mechanical properties	parameter	value	unit	norm		comment
Tensile strength	50mm/min	62	MPa	DIN EN ISO 527-2		(1) For tensile test: specimen type 1b (2) For flexural test: support span 64mm, norm specimen. (3) Specimen 10x10x10mm (4) Specimen 10x10x50mm, modulus range between 0.5 and 1% compression. (5) For Charpy test: support span 64mm, norm specimen.
Modulus of elasticity (tensile test)	1mm/min	3500	MPa	DIN EN ISO 527-2	1)	
Tensile strength at yield	50mm/min	62	MPa	DIN EN ISO 527-2		
Elongation at yield (tensile test)	50mm/min	7	%	DIN EN ISO 527-2		
Elongation at break (tensile test)	50mm/min	9	%	DIN EN ISO 527-2		
Flexural strength	2mm/min, 10 N	98	MPa	DIN EN ISO 178	2)	
Modulus of elasticity (flexural test)	2mm/min, 10 N	3400	MPa	DIN EN ISO 178		
Compression strength	1% / 2% / 5% 5mm/min, 10 N	22/41/77	MPa	EN ISO 604	3)	
Compression modulus	5mm/min, 10 N	1600	MPa	EN ISO 604	4)	
Impact strength (Charpy)	max. 7,5J	37	kJ/m^2	DIN EN ISO 179-1eU	5)	
Notched impact strength (Charpy)	max. 7,5J	4	kJ/m^2	DIN EN ISO 179-1eA		
Shore hardness	D	83		DIN EN ISO 868		

Thermal properties	parameter	value	unit	norm		comment
Glass transition temperature	DSC	39	°C	DIN EN ISO 11357		(1) Found in public sources. Individual testing regarding application conditions is mandatory.
Melting temperature		224	°C	DIN EN ISO 11357		
Service temperature	short term	200	°C		1)	
Service temperature	long term	110	°C			
Thermal expansion (CLTE)	23-60°C, long.	8	10^{-5} K^{-1}	DIN EN ISO 11359-1;2		
Thermal expansion (CLTE)	23-100°C, long.	10	10^{-5} K^{-1}	DIN EN ISO 11359-1;2		

Other properties	parameter	value	unit	norm		comment
Water absorption	24h / 96h (23°C)	0.03 / 0.05	%	DIN EN ISO 62	1)	(1) Ø ca. 50mm, h=13mm (2) - poor resistance (3) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Resistance to hot water/ bases		-		-	2)	
Resistance to weathering		-				
Flammability (UL94)	corresponding to	HB		DIN IEC 60695-11-10;	3)	

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.

Manufactured by: Ensinger Group, a German based plastic manufacturer

Represented by:
Ensinger Asia Holding Pte Ltd. (Singapore Branch)
for Asia Pacific other than Japan+China

63 Hillview Avenue #02-03
Lam Soon Industrial Building
Singapore 669569
Tel +65 65524177
Fax +65 65525177
www.ensingerplastics.com/en-sg/

Date: 2023/07/19

Version: AB