

TECAFIL PA6 GF30 black - Filament

Chemical Designation

PA 6 (Polyamide 6)

Colour

black

Density

1.36 g/cm³

Fillers

glass fibres

Main features

→ Standard spool body: OD Ø 200mm, width 55mm, Take up Ø52mm

<i>Mechanical properties</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Tensile strength	50 mm/min	155	MPa	DIN EN ISO 527-1	
Modulus of elasticity (tensile test)	50 mm/min	9200	MPa	DIN EN ISO 527-1	
Elongation at break (tensile test)	50 mm/min	4,2	%	DIN EN ISO 527-1	
Impact strength (Charpy)		55	kJ/m ²	DIN EN ISO 179-1eU	
<i>Thermal properties</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Glass transition temperature		5 / 60	°C	DIN 53765	1) (1) moist/dry
Melting temperature		220	°C	DIN 53765	
Service temperature	long term	100	°C	-	
Service temperature	short term	180	°C	-	
<i>Other properties</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Viscosity number		230	ml/g	DIN EN ISO 307	
<i>Predrying</i>	<i>parameter</i>	<i>value</i>	<i>unit</i>	<i>norm</i>	<i>comment</i>
Permissible residual moisture content		< 0,1	%	-	
Drying temperature		80	°C	-	
Drying time		4-8	h	-	

Our information and statements reflect to current state of our knowledge and shall inform about the products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our standard products are not intended to be used in specially regulated markets with applications such as medical (especially medical and dental implants), drinking water, food, toys and cosmetics. Existing commercial patents have to be observed. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at ensingerplastics.com. Technical changes reserved. This variety complies with RoHS Directive 2011/65/EU as amended. European-made or imported varieties comply with REACH Regulation 1907/2006 / EC as amended. Unless otherwise noted, these values were determined by tests on injection moulded samples, dry as moulded. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. In order to achieve optimum mechanical properties, pre-drying of the material is recommended with the parameters mentioned above. Filaments should preferably be stored in dry rooms at normal temperatures and be protected from direct sunlight.