

# TECAPEEK CMP natural - Stock Shapes (rods, plates, tubes)

## Chemical Designation

PEEK (Polyetheretherketone)

## Colour

beige opaque

## Density

1.31 g/cm<sup>3</sup>

The values in this data sheet are tested on a dimension outside of the standard reference dimension (rod Ø 40-60 mm).

## Main features

- good heat deflection temperature
- good machinability
- inherent flame retardant
- hydrolysis and superheated steam resistant
- resistance against high energy radiation
- good slide and wear properties
- high toughness
- high creep resistance

## Target Industries

- semiconductor technology

Mechanical properties	condition	value	unit	test method	comment
Tensile strength	50mm/min	110	MPa	DIN EN ISO 527-2	
Modulus of elasticity (tensile test)	1mm/min	4100	MPa	DIN EN ISO 527-2	1)
Tensile strength at yield	50mm/min	110	MPa	DIN EN ISO 527-2	
Elongation at yield (tensile test)	50mm/min	4	%	DIN EN ISO 527-2	
Elongation at break (tensile test)	50mm/min	50	%	DIN EN ISO 527-2	
Flexural strength	2mm/min, 10 N	160	MPa	DIN EN ISO 178	2)
Modulus of elasticity (flexural test)	2mm/min, 10 N	3900	MPa	DIN EN ISO 178	
Compression strength	1% / 2% 5mm/min, 10 N	15 / 34	MPa	EN ISO 604	3)
Compression modulus	5mm/min, 10 N	3200	MPa	EN ISO 604	4)
Impact strength (Charpy)	max. 7,5J	n.b.	kJ/m <sup>2</sup>	DIN EN ISO 179-1eU	5)
Notched impact strength (Izod)		4	kJ/m <sup>2</sup>	DIN EN ISO 179-1eA	
Ball indentation hardness		240	MPa	ISO 2039-1	6)
Thermal properties	condition	value	unit	test method	comment
Glass transition temperature		151	°C	DIN EN ISO 11357	
Melting temperature		340	°C	DIN EN ISO 11357	
Heat distortion temperature	HDT, Method A	162	°C	ISO-R 75 Method A	
Service temperature	short term	300	°C		1)
Service temperature	long term	260	°C		
Thermal expansion (CLTE)	23-60°C, long.	5	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	23-100°C, long.	6	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	100-150°C, long.	7	10 <sup>-5</sup> K <sup>-1</sup>	DIN EN ISO 11359-1;2	
Specific heat		1.1	J/(g*K)	ISO 22007-4:2008	
Thermal conductivity		0.27	W/(K*m)	ISO 22007-4:2008	
Electrical properties	condition	value	unit	test method	comment
surface resistivity	Silver electrode, 23°C, 12% r.h.	10 <sup>15</sup>	Ω/square	DIN IEC 60093	1)
volume resistivity	Silver electrode, 23°C, 12% r.h.	10 <sup>15</sup>	Ω*cm	DIN IEC 60093	(1) Specimen in 20mm thickness (2) Specimen in 1mm thickness
Dielectric strength	23°C, 50% r.h.	73	kV/mm	ISO 60243-1	2)
Resistance to tracking (CTI)	Platin electrode, 23°C, 50% r.h., solvent A	125	V	DIN EN 60112	
Other properties	condition	value	unit	test method	comment
Water absorption	24h / 96h (23°C)	0.02 / 0.03	%	DIN EN ISO 62	1) (1) Ø ca. 50mm, h=13mm (2) + good resistance (3) - poor resistance
Resistance to hot water/ bases		+	-		2)
Resistance to weathering		-	-		3)

→ TECAPEEK products are based on Victrex® PEEK polymer.

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at [www.ensingerplastics.com](http://www.ensingerplastics.com).