

TECASINT 6062 black - Direkt formning

Kemisk beteckning

PI (polyimid)

Färg

Svart

Densitet

1.51 g/cm³

Fillers

grafit, PTFE

Produktionsprocess: direktformning

Huvud egenskaper

- utmärkta slip-stick egenskaper
- mycket bra glid- och slitegenskaper
- motstånd mot hög energi strålning
- bra kemisk resistans
- känslig för hydrolys i högre termiska intervall

Målindustrier

- maskinteknik
- bilindustrin
- flygplan och rymdteknik

Mekaniska Egenskaper	parameter	värde	enhet	norm	anmärkning
Draghållfasthet	50 mm/min	50	MPa	DIN EN ISO 527-1	
Elasticitetsmodul (dragprov)	1 mm/min	4100	MPa	DIN EN ISO 527-1	
Brottförlängning	50 mm/min	2.1	%	DIN EN ISO 527-1	
Böjghållfasthet	10 mm/min	75	MPa	DIN EN ISO 178	
Elasticitetsmodul (böjningstest)	2 mm/min	4200	MPa	DIN EN ISO 178	
Brottförlängning (böjtest)	10 mm/min	2.3	%	DIN EN ISO 178	
Kompressionsstyrka	10 mm/min	125	MPa	EN ISO 604	
Kompressionsstyrka	10mm/min, 10% strain	120	MPa	EN ISO 604	
tryckhållfasthet vid brott	10 mm/min	17	%	EN ISO 604	
Shore hårdhet	Shore D	82		DIN EN ISO 868	
Värmeledningsförmåga	parameter	värde	enhet	norm	anmärkning
Glasövergångstemperatur		286	°C	-	1) (1) DMA, maximum loss factor tan δ
termisk expansion	50-200°C	2.2 / -	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	2) (2) Thermal expansion XY/Z axis
termisk expansion	200-300°C	5.8 / -	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1;2	3) (3) Thermal expansion XY/Z axis
Övriga egenskaper	parameter	värde	enhet	norm	anmärkning
Vatten absorption	24 h in water, 23°C	0.2	%	DIN EN ISO 62	(1) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Brandklassning (UL94)	corresponding to	V0		DIN IEC 60695-11-10;	1)

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.