

TECAFIL PEEK VX CF30 black - Filament

Chemical Designation

PEEK (Poly etheretherketone)

Colour

black

Density

1.38 g/cm³ (*2)

Fillers

30% carbon fibres

Target Industries

- oil and gas industry
- automotive industry
- chemical technology
- mechanical engineering
- aircraft and aerospace technology

General material information					
parameter	value	unit	norm	comment	
Diameter	1,75 +/- 0,05	mm	-	(1) standard spool body	
Spool Measurements holder	Ø 52	mm	-	(2) do not dry spool >120°C (3) Ø 1,75mm	
Spool Measurements outer diameter	Ø 200	mm	-	1)	
Spool Measurements width	55	mm	-		
Spool Material	Polycarbonate	-	-	2)	
Filament Load per Spool	500	g	-		
Filament Length per Spool	141	m	-	3)	
Mechanical properties					
parameter	value	unit	norm	comment	
Tensile strength 50 mm/min	190	MPa	DIN EN ISO 527-1	1) (*1)	
Modulus of elasticity (tensile test) 50 mm/min	17500	MPa	DIN EN ISO 527-1	2) (*1)	
Elongation at break (tensile test) 50 mm/min	2	%	DIN EN ISO 527-1	3) (*1)	
Flexural strength 2 mm/min, 10 N	-	MPa	DIN EN ISO 178	4) (*1)	
Modulus of elasticity (flexural test) 2 mm/min, 10 N	-	MPa	DIN EN ISO 178	5) (*1)	
Elongation at break (flexural test) 2 mm/min, 10 N	-	%	DIN EN ISO 178	6) (*1)	
Impact strength (Charpy) max 7,5J - 23°C	45	kJ/m ²	DIN EN ISO 179-1eU	7) (*1)	
Notched impact strength (Charpy) max 7,5J - 23°C	-	kJ/m ²	DIN EN ISO 179-1eA	8) (*1)	
Thermal properties					
parameter	value	unit	norm	comment	
Glass transition temperature	143	°C	ASTM D 3418	1) (*2)	
Melting temperature	343	°C	DIN EN ISO 11357	2) (*2)	
Deflection temperature HDT-A	162	°C	ISO-R 75 Method A	3) (*2)	
Service temperature long term	260	°C	-	4) (*2)	
Service temperature short term	300	°C	-	5) (*2)	
Thermal expansion (CLTE)	4	10 ⁻⁵ K ⁻¹	DIN EN ISO 11359-1,2	6) (*2)	
Other properties					
parameter	value	unit	norm	comment	
Moisture absorption	0,03	%	DIN EN ISO 62	1) (*2)	
Melt flow index (MFI)	-	g/10 min	DIN EN ISO 1133	2) (*2)	
Processing parameter					
parameter	value	unit	norm	comment	
Nozzle temperature	400 - 440	°C	-	(1) required	
Max. melt temperature	450	°C	-		
Print bed temperature	130 - 160	°C	-		
Build chamber temperature	230 - 250	°C	-	1)	
Nozzle diameter	0,4 - 0,6	mm	-		
Print speed	20 - 30	mm/s	-		
Fan speed	0	%	-		
Predrying					
parameter	value	unit	norm	comment	
Drying temperature	120	°C	-	1) (*4)	
Drying time	8	h	-		

→ To achieve optimum mechanical properties, it is recommended to pre-dry the material with the above mentioned parameters.

- (*1) Values measured on injection moulded test specimens
- (*2) Values measured on the raw material
- (*3) The exact parameters depend on the printer used.
- (*4) Do not exceed maximum drying temperature of 120°C
- (*5) Properties tested on printed specimens
- (*6) Specimens printed on Minifactory Ultra

→ The filament should preferably be stored in dry, normal temperature rooms and protected from direct sunlight.

Our information and statements reflect to current state of our knowledge and shall inform about the products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at ensingerplastics.com. Technical changes reserved. European-made or imported varieties comply with REACH Regulation 1907/2006 / EC as amended. Unless otherwise noted, these values were determined by tests on injection moulded samples, dry as moulded. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. In order to achieve optimum mechanical properties, pre-drying of the material is recommended with the parameters mentioned above. Filaments should preferably be stored in dry rooms at normal temperatures and be protected from direct sunlight.