

TECAPEEK® ELS nano black - Stock Shapes (rods, plates, tubes)

Chemical Designation

PEEK (Polyetheretherketone)

Colour

black opaque

Density

1.36 g/cm³

Fillers

CNT

Main features

- high dimensional stability
- high continuous use temperature
- high strength
- very good chemical resistance
- electrically conductive
- high thermal and mechanical capacity
- good machinability
- high toughness

Target Industries

- aircraft and aerospace technology
- electronics
- mechanical engineering
- semiconductor technology
- computer technology

Mechanical properties	condition	value		test method	comment
Tensile strength	2 in/min	15400	psi	DIN EN ISO 527-2	(1) For tensile test: specimen type 1b
Modulus of elasticity (tensile test)	0.039 in/min	696000	psi	DIN EN ISO 527-2	1) (2) For flexural test: support span 2.52", norm specimen.
Tensile strength at yield	2 in/min	15400	psi	DIN EN ISO 527-2	(3) Specimen 0.39" x 0.39" x 0.39"
Elongation at yield (tensile test)	2 in/min	4	%	DIN EN ISO 527-2	(4) Specimen 0.39" 0.39" x 0.39"
Elongation at break (tensile test)	2 in/min	4	%	DIN EN ISO 527-2	(5) Specimen 0.39" x 0.39" x 0.39"
Flexural strength	0.078 in/min, 2.25 lbf	25800	psi	DIN EN ISO 178	2) (6) Specimen 0.39" x 0.39" x 1.97", modulus range between 0.5 and 1% compression.
Modulus of elasticity (flexural test)	0.078 in/min, 2.25 lbf	682000	psi	DIN EN ISO 178	(7) For Charpy test: support span 2.52", norm specimen.
Compression strength	2% strain 0.197 in/min, 2.25 lbf	6820	psi	EN ISO 604	3) (8) Specimen in 0.157" thickness
Compression strength	5% strain 0.197 in/min, 2.25 lbf	15400	psi	EN ISO 604	4)
Compression strength	1% strain 0.197 in/min, 2.25 lbf	3920	psi	EN ISO 604	5)
Compression modulus	0.197 in/min, 2.25 lbf	522000	MPa	EN ISO 604	6)
Impact strength (Charpy)	ft-lbs/in ²	27.6		DIN EN ISO 179-1eU	7)
Ball indentation hardness		36700	psi	ISO 2039-1	8)
Thermal properties	condition	value		test method	comment
Glass transition temperature		297	°F	DIN EN ISO 11357	1) (1) Found in public sources.
Melting temperature		646	°F	DIN EN ISO 11357	(2) Found in public sources.
Service temperature	short term	572	°F	-	2) Individual testing regarding application conditions is mandatory.
Service temperature	long term	500	°F	-	
Thermal expansion (CLTE)	73 - 140°F, long.	2.78	*10 ⁻⁵ in/in/°F	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	73 - 212°F, long.	2.78	*10 ⁻⁵ in/in/°F	DIN EN ISO 11359-1;2	
Thermal expansion (CLTE)	212 - 300°F, long.	3.89	*10 ⁻⁵ in/in/°F	DIN EN ISO 11359-1;2	
Specific heat		0.00026	BTU/lb-F°	ISO 22007-4:2008	
Thermal conductivity		3.19	BTU-in/hr-ft ² -°F	ISO 22007-4:2008	
Electrical properties	condition	value		test method	comment
surface resistivity	Conductive rubber, 73°F, 12% r.h.	10 ² - 10 ⁴	Ω	DIN EN 61340-2-3	1) (1) Specimen in 0.787" thickness
volume resistivity	Conductive rubber, 73°F, 12% r.h.	10 ³ - 10 ⁵	Ω*cm	DIN EN 61340-2-3	
Other properties	condition	value		test method	comment
Water absorption	24h / 96h (73°F)	0.02 / 0.03	%	DIN EN ISO 62	1) (1) Ø ca. 1.57", h=0.512" (2) + good resistance
Resistance to hot water/ bases		+		-	2) (3) (+) limited resistance
Resistance to weathering		(+)		-	3) (4) Corresponding means no listing at UL (yellow card).
Flammability (UL94)	corresponding to	V0		DIN IEC 60695-11-10;	4) The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.

→ TECAPEEK products are based on Victrex® PEEK polymer.

This information reflects the current state of our knowledge and is intended only to assist and advise. It is given without obligation or liability. It does not assure or guarantee chemical resistance, quality of products or their suitability in any legally binding way. Values are not minimum or maximum values, but guidelines that can be used for comparative purposes in material selection. They are within the normal range of product properties and do not represent guaranteed property values. Testing under individual application circumstances is always recommended. Data is obtained from extruded shapes material unless otherwise noted. References to FDA compliance refer to the resins from which the products were made unless otherwise noted. All trade and patent rights should be observed. All rights reserved. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com.

