

TECASINT 4011 natural - Stock Shapes (rods, plates, tubes)

Chemical Designation

PI (Polyimide)

Colour

yellow

Density

1.42 g/cm³

Main features

- very high thermal and oxidative resistance
- very low water absorption
- high thermal and mechanical capacity
- high creep resistance
- low outgassing
- good chemical resistance
- resistance against high energy radiation
- sensitive to hydrolysis in higher thermal range

Target Industries

- mechanical engineering
- precision engineering
- electronics
- electrical engineering
- conveyor technology
- semiconductor technology

Mechanical properties	condition	value	unit	test method	comment
Tensile strength	0.40 inch/min	134	MPa	ASTM D 638	(1) eU
Modulus of elasticity (tensile test)	0.04 inch/min	4083	MPa	ASTM D 638	(2) eA (3) Specimen in 4mm thickness
Elongation at break (tensile test)	0.40 inch/min	6.9	%	ASTM D 638	
Flexural strength	0.54 inch/min	207	MPa	ASTM D 790	
Modulus of elasticity (flexural test)	0.54 inch/min	4299	MPa	ASTM D 790	
Compression strength	0.05 inch/min, 10% strain	188	MPa	ASTM D 695	
Compression modulus	0.05 inch/min	4325	MPa	ASTM D 695	
Impact strength (Charpy)	max 7.5 J	87	kJ/m ²	DIN EN ISO 179-1	1)
Notched impact strength (Charpy)	max 7.5 J	9.6	kJ/m ²	DIN EN ISO 179-1	2)
Shore hardness	Shore D	88		DIN EN ISO 868	
Ball indentation hardness		265	MPa	ISO 2039-1	3)
Thermal properties	condition	value	unit	test method	comment
Glass transition temperature		500	°F	DIN EN ISO 11357	(1) Thermal expansion XY/Z axis
Heat distortion temperature	1.82 MPa	680	°F	ASTM D 648	(2) Thermal expansion XY/Z axis
Thermal expansion (CLTE)	122-392°F	46 / 56	10 ⁻⁶ K ⁻¹	DIN 53 752	1) (3) Thermal expansion XY/Z axis
Thermal expansion (CLTE)	392-572°F	62 / 76	10 ⁻⁶ K ⁻¹	DIN 53 752	2)
Thermal expansion (CLTE)	572-662°F	85 / 112	10 ⁻⁶ K ⁻¹	DIN 53 752	3)
Specific heat		1.22	J/(g*K)	ASTM E1461	
Thermal conductivity	104°F	0.4	W/(K*m)	ASTM E1461	
Electrical properties	condition	value	unit	test method	comment
surface resistivity	73°F	10 ¹⁶	Ω	ASTM D 257	
volume resistivity	73°F	10 ¹⁶	Ω*cm	ASTM D 257	
Electric strength DC	73°F	18	kV*mm ⁻¹	ASTM D 149	
Dielectric loss factor	1 kHz	1*10 ⁻³		ASTM D 150	
Dielectric constant	1 kHz	3.59		ASTM D 150	
Other properties	condition	value	unit	test method	comment
Water absorption	24 h in water, 73°F	0.16	%	DIN EN ISO 62	(1) Corresponding means no listing at UL (yellow card). The information might be taken from resin, stock shape or estimation. Individual testing regarding application conditions is mandatory.
Water absorption	24 h in water, 176°F	0.6	%	DIN EN ISO 62	
Outgassing in high vacuum		passed		ECSS-Q-70-02	
Flammability (UL94)	corresponding to	V0		DIN IEC 60695-11-10;	1)
Oxygen Index		49	%	EN ISO 4589-2	

Our information and statements reflect the current state of our knowledge and shall inform about our products and their applications. They do not assure or guarantee chemical resistance, quality of products and their merchantability in a legally binding way. Our products are not defined for use in medical or dental implants. Existing commercial patents have to be observed. The corresponding values and information are no minimum or maximum values, but guideline values that can be used primarily for comparison purposes for material selection. These values are within the normal tolerance range of product properties and do not represent guaranteed property values. Therefore they shall not be used for specification purposes. Unless otherwise noted, these values were determined by tests at reference dimensions and machined specimen. As the properties depend on the dimensions of the semi-finished products and the orientation in the component (esp. in reinforced grades), the material may not be used without a separate testing under individual circumstances. The customer is solely responsible for the quality and suitability of products for the application and has to test usage and processing prior to use. Data sheet values are subject to periodic review, the most recent update can be found at www.ensingerplastics.com. Technical changes reserved.